



Standard Specification for Stranded Carbon Steel Wire Ropes for General Purposes¹

This standard is issued under the fixed designation A1023/A1023M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the general requirements for the more common types of stranded steel wire ropes. Included in this specification are wire ropes in various grades and constructions from 1/4 in. [6 mm] to 2 3/8 in. [60 mm] manufactured from uncoated or metallic coated wire. Also included are cord products from 1/32 in. [0.8 mm] to 3/8 in. [10 mm] manufactured from metallic coated wire. For specific applications, additional or alternative requirements may apply.

1.2 The values stated in either inch-pounds or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:²

A931 Test Method for Tension Testing of Wire Ropes and Strand

A1007 Specification for Carbon Steel Wire for Wire Rope

2.2 ISO Standards:³

ISO 2232 Round Drawn Wire for General-Purpose Non-alloy Steel Wire Ropes

ISO 3108 Steel Wire Ropes for General Purposes—Determination of Actual Breaking

3. Terminology

Description of Terms Specific to this Specification

3.1 *inserts, n*—fiber or solid polymer so positioned as to separate adjacent strands or wires in the same or overlying layers or to fill interstices of the rope.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.03 on Steel Rod and Wire.

Current edition approved Oct. 1, 2009. Published December 2009. Originally approved in 2002. Last previous edition approved in 2007 as A1023/A1023M – 07. DOI: 10.1520/A1023_A1023M-09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from International Organization for Standardization (ISO), 1 rue de Varembe, Case postale 56, CH-1211, Geneva 20, Switzerland, http://www.iso.ch.

3.2 Lubrication:

3.2.1 *impregnating compound, n*—material used in the manufacture of natural fiber cores, covers, or inserts for the purpose of providing protection against rotting and decay of the fiber material.

3.2.2 *preservation compound, n*—material, usually containing some form of blocking agent, applied during, after, or both during and after manufacture of the rope to fiber inserts, fillers, and coverings for the purpose of providing protection against corrosion.

3.2.3 *rope lubricant, n*—general term used to signify material applied during the manufacture of a strand, core, or rope for the purpose of reducing internal friction, providing protection against corrosion, or both.

3.3 *rope cores, n*—central element, usually of fiber or steel (but may be a combination of both), of a round rope around which are laid helically the strands of a stranded rope or the unit ropes of a cable-laid rope (Fig. 1).

3.3.1 *fiber core (FC), n*—an element made from either natural or synthetic fibers.

3.3.2 *solid polymer core, n*—a single element of solid polymer material that is either cylindrical or shaped (grooved). It may also include an element or elements of wire or fiber.

3.3.3 *steel core, n*—a stranded rope (IWRC), or a round strand (WSC) construction. The round strand or the stranded rope core or its outer strands, or both, may also be covered or filled with either fiber or solid polymer. Steel cores are normally made as a separate independent element, the exception being rope with a stranded rope core closed parallel with the outer strands.

3.4 *strand, n*—an element of rope normally consisting of an assembly of wires of appropriate shape and dimensions laid helically in one or more layers around a center. The center may consist of one round or shaped wire, of several round wires forming a built-up center, or of fiber or some other material. If multiple wires are used in a strand center, they may be counted as one wire.

3.4.1 Cross-Section Shape:

3.4.1.1 *compacted strand, n*—a strand that has been subjected to a compacting process such as drawing, rolling, or swaging (Fig. 2).

3.4.1.2 *round strand, n*—strand having a perpendicular cross-section that is approximately the shape of a circle (Fig. 3).

*A Summary of Changes section appears at the end of this standard.




FIG. 1 Examples of Cores

Warrington layers are designated by listing the number of large and small wires with a + sign in between and bracketing () the layer, for example, (6+6) (Fig. 6d).

NOTE 1—Strand construction is designated by listing the number of wires, beginning with the outer wires, with each layer separated by a hyphen.

3.4.3.3 *single lay, n*—strand that contains only one layer of wires.

3.5 *stranded wire rope, n*—an assembly of strands laid helically in one or more layers around a core. Exceptions are stranded wire ropes consisting of three or four outer strands that may or may not be laid around a core. Elements of stranded wire rope are shown in Fig. 7.

3.6 *Wires:*

3.6.1 *finish and quality of coating, n*—the condition of the surface finish of the wire, that is, uncoated or metallic coated (zinc or zinc alloy).

3.6.1.1 *metallic coated wire, n*—carbon steel wire that has a metallic coating.

(a) *drawn-galvanized wire, n*—coated carbon steel wire with a zinc coating applied prior to the final wire drawing operation, that is, galvanized in process.

(b) *drawn-Zn5/Al-MM wire, n*—coated carbon steel wire with a zinc-aluminum alloy (mischmetal) coating applied prior to the final wire drawing operation.

(c) *final-coated Zn5/Al-MM wire, n*—coated carbon steel wire with a zinc-aluminum alloy (mischmetal) coating applied after the final wire drawing operation.

(d) *final-galvanized wire, n*—coated carbon steel wire with a zinc coating applied after the final wire drawing operation, that is, galvanized at finished size.

3.6.1.2 *uncoated wire, n*—carbon steel wire that does not have a metallic coating. Commonly referred to as bright wire.

3.6.2 *Function:*

3.6.2.1 *filler wires, n*—comparatively small wires used in certain constructions of parallel lay ropes to create the necessary number of interstices for supporting the next layer of covering wires.

3.6.2.2 *load-bearing wires (main wires), n*—those wires in a rope that are considered as contributing toward the breaking force of the rope.

3.6.2.3 *non-load-bearing wires, n*—those wires in a rope that are considered as not contributing toward the breaking force of the rope.

3.6.2.4 *seizing (serving) wires or strands, n*—single wires or strands used for making a close-wound helical serving to retain the elements of a rope in their assembled position.

3.6.3 *layer of wires, n*—an assembly of wires having one pitch diameter. The exception is a Warrington layer comprising large and small wires where the smaller wires are positioned on a larger pitch circle than the larger wires. The first layer of wires is that which is laid over the strand center. Filler wires do not constitute a separate layer.

3.6.4 *Position:*

3.6.4.1 *center wires, n*—wires positioned at the center of a strand of a stranded rope.

3.6.4.2 *core wires, n*—all wires comprising the core of a stranded rope.

3.4.1.3 *triangular strand, n*—strand having a perpendicular cross-section that is approximately the shape of a triangle (formerly referred to as flattened strand) (Fig. 4).

(a) Style B—Solid center wire

(b) Style G—3×2 or 3×2+3F center

(c) Style H—3 or 3+3F center

(d) Style V—1×7 center

3.4.2 *strand lay direction, n*—the direction right (z) or left (s) corresponding to the direction of lay of the outer wires in relation to the longitudinal axis of the strand (Fig. 5).

3.4.3 *Type and Constructions:*

3.4.3.1 *multiple operation lay, n*—construction containing at least two layers of wires in which successive layers are laid in more than one operation, with different lay lengths. There are two basic types of multiple operation strand:

(a) *compound lay, n*—strand that contains a minimum of three layers of wires where a minimum of one layer is laid in a separate operation, but in the same direction, over a parallel lay center.

(b) *cross-lay, n*—strand in which the wires are laid in the same direction. The wires of superimposed wire layers cross one another and make point contact.


3.4.3.2 *parallel lay, n*—strand that contains at least two layers of wires, all of which are laid in one operation (in the same direction). The lay length of all the wire layers is equal, and the wires of any two superimposed layers are parallel to each other, resulting in linear contact. There are four types of parallel lay constructions:

(a) *combined, adj*—describes a parallel lay construction having three or more layers laid in one operation and formed from a combination of the above, for example, Warrington-Seale construction (Fig. 6a).

(b) *filler (F), adj*—describes a construction having outer layer containing twice the number of wires than the inner layer, with filler wires laid in the interstices between the layers. Filler wires are designated with the letter “F” (Fig. 6b).

(c) *Seale (S), adj*—describes a construction having same number of wires in each layer, for example, 9-9-1 (Fig. 6c).

(d) *Warrington (W), adj*—describes a construction having outer (Warrington) layer containing alternately large and small wires and twice the number of wires as the inner layer.



Strand Before Compacting Strand After Compacting

FIG. 2 Compacted Round Strand—Before and After




FIG. 3 Round Strand




FIG. 4 Triangular Strand



Right Lay (z)



Left Lay (s)

FIG. 5 Lay Direction of Strands for Stranded Ropes

3.6.4.3 *inner wires, n*—all wires except center, filler, core, and outer wires in a stranded rope.

3.6.4.4 *outer wires, n*—all wires in the outer layer of the outer strands of a stranded rope.

Dimensional Characteristics

3.7 *Diameter of Rope:*

3.7.1 *diameter of plastic-coated rope, n*—the diameter that circumscribes the overall rope cross-section including the

cover followed by the diameter, which circumscribes the underlying rope (for example, $\frac{3}{4} \times \frac{5}{8}$ in.).

3.7.2 *diameter of round rope, n*—the diameter (d) that circumscribes the rope cross-section. Diameter is expressed in inches or millimeters (Fig. 8).

3.8 *Lay Length:*

3.8.1 *rope lay length, n*—that distance measured parallel to the longitudinal rope axis in which the outer strands of a stranded rope or the component ropes of a cable-laid rope make one complete turn (or helix) about the axis of the rope (Fig. 9).

3.8.2 *strand lay length, n*—that distance measured parallel to the longitudinal strand axis, in which the wire in the strand makes one complete turn (or helix) about the axis of the strand. The lay length of a strand is that corresponding to the outer layers of wires (Fig. 9).

Manufacture (Rope)

3.9 *Preformation:*

3.9.1 *non-preformed rope, n*—rope in which the wires and strands in the rope will, after removal of any seizing (serving), spring out of the rope formation.

3.9.2 *preformed rope, n*—rope in which the wires and strands in the rope will not, after removal of any seizing (serving), spring out of the rope formation.

3.10 *prestretching, n*—the name given to a process that results in the removal of a limited amount of constructional stretch.

Mechanical Properties

3.11 *Rope:*


3.11.1 *actual (measured) breaking force, n*—breaking force obtained using the prescribed test method in Test Method A931 or ISO 3108.

3.11.2 *calculated breaking force, n*—value of breaking force obtained from the sum of the measured breaking forces of the wires in the rope, before rope making, multiplied by the measured spinning loss factor as determined by the rope manufacturer's design.

3.11.3 *measured spinning loss factor, n*—ratio between the measured breaking force of the rope and the sum of the measured breaking forces of the wires, before rope making.

3.11.4 *minimum breaking force, n*—specified value that the actual (measured) breaking force must meet or exceed in a prescribed test.

3.12 *Rope Stretch (Extension):*



A—Example of Combined Parallel Lay ex. 31WS, 12-(6+6)-6-1
 B—Filler Construction ex. 25F, 12-6F-6-1
 C—Seale Construction ex. 19S, 9-9-1
 D—Warrington Construction ex. 19W, (6+6)-6-1

FIG. 6 Parallel Lay Constructions




FIG. 7 Elements of Stranded Wire Rope




FIG. 8 Diameter of Round Rope

3.12.1 *constructional stretch (extension), n*—amount of extension that is attributed to the initial bedding down of wires

within the strands and the strands within the rope due to loading. Initial extension cannot be determined by calculation.

3.12.2 *elastic stretch (extension), n*—amount of recoverable extension that follows Hooke’s law within certain limits due to application of a load.

3.12.3 *permanent stretch (extension), n*—non-elastic extension.

3.13 *Wire:*

3.13.1 *torsions, n*—a measure of wire ductility normally expressed as the number of 360° revolutions that a wire can withstand before breakage occurs, using a prescribed test method. Torsion requirements are based on the wire diameter and either the wire level, as specified in Specification A1007, or the tensile strength grade, as specified in ISO 2232.

3.13.2 *wire tensile strength, n*—ratio between the maximum force obtained in a tensile test and the nominal cross-sectional area of the test piece. Requirements for wire tensile strength are determined by either the wire level, as specified in Specification A1007, or by the tensile strength grade, as specified in ISO 2232.

3.13.2.1 *tensile strength grade, n*—a level of requirement for tensile strength based on the SI system of units. It is designated by a value according to the lower limit of tensile strength and is used when specifying wire. Values are expressed in N/mm² (for example, 1960).

3.13.2.2 *wire level, n*—a level of requirement for tensile strength based on the inch-pound system of units (for example, Level 3).

Terminology Relating to Ropes

3.14 *Rope Classification and Construction:*

3.14.1 *rope classification, n*—a grouping of ropes of similar characteristics on the basis of, for stranded ropes, the number of strands and their shape, the number of strand layers, the number of wires in one strand, the number of outer wires in one strand, and the number of wire layers in one strand. For classification details, refer to Table 2.

3.14.2 *rope construction, n*—detail and arrangement of the various elements of the rope, taking into account the number of




FIG. 9 Lay Lengths

TABLE 1 Wire Tensile Strength Grades or Levels for Given Rope Grades

Rope Grade	Wire Tensile Strength Grade or Level	
	Minimum	Maximum
IPS	Level 2 / 1570	Level 4 / 1960
EIP	Level 3 / 1770	Level 5 / 2160
EEIP	Level 4 / 1960	Level 5 / 2160
1770	1570 / Level 2	1960 / Level 4
1960	1770 / Level 3	2160 / Level 5
2160	1960 / Level 4	2160 / Level 5

TABLE 3 Weight of Coating for Final-Galvanized or Final-Coated Zn-5Al-MM Rope Wire

Diameter of Wire		Minimum Weight of Coating	
in.	[mm]	oz/ft ²	[kg/m ²]
0.025 to 0.047 incl	0.64 to 1.19 incl	0.20	0.06
over 0.047 to 0.054 incl	over 1.19 to 1.37 incl	0.40	0.12
over 0.054 to 0.063 incl	over 1.37 to 1.60 incl	0.50	0.15
over 0.063 to 0.079 incl	over 1.60 to 2.01 incl	0.60	0.18
over 0.079 to 0.092 incl	over 2.01 to 2.34 incl	0.70	0.21
over 0.092 to 0.192 incl	over 2.34 to 4.88 incl	0.80	0.24

TABLE 2 Classification

Classification	Table		Diameter (in.)	Diameter [mm]
	SC	FC		
6×7	9	10	¼ -1½	6-36
6×19	11	12	¼ -2¾	6-60
6×36	13	14	¼ -2¾	6-60
7×19	15		¼ -2¾	6-60
7×36	16		¼ -2¾	6-60
8×19	17		¼ -2¾	6-60
8×36	18		¼ -2¾	8-60
8×19 SR	19		½ -1½	12-38
19×7	20		¼ -1½	6-36
34×7	21		¼ -1½	8-40
35×7	22		⅜ -1½	8-40
6×12		23	⅝ -1	8-25
6×24		24	⅝ -2	9.5-51
6×25 TS	25	26	½ -2¾	12-60
6×19 CS	27		⅜ -2¼	10-56
6×36 CS	28		⅜ -2¼	10-56
6×19 SW	29		½ -1½	12-38
6×36 SW	30		½ -1½	12-38
19×7 CS	31		¼ -1	6-24
19×19	32		⅜ -1½	10-40
35×7 CS	33		⅞ -1½	10-40
3×7 CORD	34		1/32	0.8
7×7 CORD	34		⅜ -3/8	1.2-9.5
7×19 CORD	34		1/16 -3/8	1.6-9.5

Designation key:

- SR = spin resistant
- TS = triangular strand
- CS = compacted strand
- SW = swaged rope
- CORD = small diameter specialty wire rope
- SC = steel core
- FC = fiber core

TABLE 4 Weight of Coating for Drawn-Galvanized or Drawn Zn-5Al-MM Rope Wire

Diameter of Wire		Minimum Weight of Coating	
in.	[mm]	oz/ft ²	[kg/m ²]
0.0045 to 0.010 incl	0.11 to 0.25 incl	0.03	0.009
Over 0.010 to 0.017 incl	Over 0.25 to 0.43 incl	0.05	0.015
over 0.017 to 0.028 incl	over 0.43 to 0.71 incl	0.10	0.03
over 0.028 to 0.060 incl	over 0.71 to 1.52 incl	0.20	0.06
over 0.060 to 0.090 incl	over 1.52 to 2.29 incl	0.30	0.09
over 0.090 to 0.140 incl	over 2.29 to 3.56 incl	0.40	0.12

TABLE 5 Tolerances on Rope Diameter (Stranded Rope) (Inch-Pound Units)

Nominal Rope Diameter (d), in.	Diameter Tolerances as a Percentage of Nominal Diameter
thru 1/8	-0, +8 %
over 1/8 thru 3/16	-0, +7 %
over 3/16 thru 5/16	-0, +6 %
over 5/16 and larger ^A	-0, +5 %

^A 6×12 and 6×24 classifications -0, +7 % (Tables 24 and 25)

TABLE 6 Tolerances on Rope Diameter (Stranded Rope) [SI Units]

Nominal Rope Diameter (d), [mm]	Diameter Tolerances as a Percentage of Nominal Diameter
from 2 to <4	-0, +8 %
from 4 to <6	-0, +7 %
from 6 to <8	-0, +6 %
8 and greater	-0, +5 %

strands, and the number of wires in the strand. For construction details, refer to Tables 9–34.

3.14.3 Discussion—Rope construction is designated by listing the number of outer strands followed by the number of wires in each strand and the designation for the type of construction, for example, 6×25F. The “×” symbol is read as “by.”

3.15 rope grade, n—a level of requirement for breaking force that is designated either by a number (for example, 1770,

1960) or a series of letters (for example, IPS, EIP). See 6.3. Rope grade does not imply that the actual tensile strength of the wires in the rope is necessarily of this grade.

3.16 Rope Lay:

3.16.1 lay direction of rope, n—the direction right (Z) or left (S) corresponding to the direction of lay of the outer strands in a stranded rope or the unit ropes in a cable laid rope in relation to the longitudinal axis of the rope.

3.16.2 Lay Types:

3.16.2.1 alternate lay, adj—describes stranded rope in which the type of lay of the outer strands is alternately regular

TABLE 7 Permissible Differences in Rope Diameter (Inch-Pound Units)

Nominal Rope Diameter (d), in.	Percentage Allowable Difference (%)
1/8 and smaller	7
over 1/8 thru 3/16	6
over 3/16 thru 5/16	5
over 5/16 and larger	4

TABLE 8 Permissible Differences in Rope Diameter [SI Units]

Nominal Rope Diameter (d), [mm]	Percentage Allowable Difference (%)
from 2 to <4	7
from 4 to <6	6
from 6 to <8	5
8 and greater	4

(ordinary) lay followed by lang lay such that half of the outer strands are regular (ordinary) lay and the other half are lang lay. The lay direction of the rope will be either right (AZ) or left (AS). Alternate lay can also be supplied with two lang lay strands followed by one regular (ordinary) lay strand in a repeating pattern.

3.16.2.2 *contra-lay, adj*—describes rope in which at least one layer of strands is laid in the opposite direction to the other layers.

3.16.2.3 *lang lay, adj*—describes stranded rope in which the direction of lay of the wires in the outer strands is the same direction as that of the outer wires in the rope (Fig. 10).

3.16.2.4 *regular (ordinary), adj*—describes stranded rope in which the direction of lay of the wires in the outer strands is in the opposite direction to the lay of the outer strands in the rope.

3.16.3 *Discussion*—The lower case letter denotes strand direction; the upper case letter denotes rope direction.

3.17 *Rope Types:*

3.17.1 *cable-laid rope, n*—an assembly of several (usually six) round stranded ropes laid helically over a core (usually a seventh rope). Requirements for cable-laid rope are not covered in this standard.

3.17.2 Ropes incorporating filling and covering materials:

3.17.2.1 *cushioned rope, n*—rope in which the inner layers, inner strands or core strands are covered with solid polymers or fibers to form a cushion between adjacent strands or overlying layers.

3.17.2.2 *plastic-coated core rope, n*—rope in which the core is covered, or filled and covered, with a solid polymer.

3.17.2.3 *plastic-coated rope, n*—rope in which the exterior surface is coated (covered) with a solid polymer.

3.17.2.4 *plastic-filled rope, n*—rope in which the free spaces up to the diameter of the rope are filled with a solid polymer.

3.17.3 *rotation-resistant rope, n*—stranded ropes designed to generate reduced levels of torque and rotation when loaded and comprising an assembly of two or more layers of strands laid helically around a center, the direction of lay of the outer strands being opposite to that of the underlying layer. There are three categories of rotation-resistant rope:

3.17.3.1 *category 1, adj*—describes stranded rope constructed in such a manner that it displays little or no tendency to rotate, or, if guided, transmits little or no torque, has at least fifteen outer strands and comprises an assembly of at least three layers of strands laid helically over a center in two operations, the direction of lay of the outer strands being opposite to that of the underlying layer.

3.17.3.2 *category 2, adj*—stranded rope constructed in such a manner that it has significant resistance to rotation, has at least ten outer strands, and comprises an assembly of two or more layers of strands laid helically over a center in two or




FIG. 10 Regular (Ordinary Lay) and Lang Lay

three operations, the direction of lay of the outer strands being opposite to that of the underlying layer.

3.17.3.3 *category 3, adj*—stranded rope constructed in such a manner that it has limited resistance to rotation, has no more than nine outer strands, and comprises an assembly of two layers of strands laid helically over a center in two operations, the direction of lay of the outer strands being opposite to that of the underlying layer.

3.17.4 *Discussion*—Rotation resistant ropes have previously been referred to as multi-strand and non-rotating ropes.

3.17.5 *Discussion*—Ropes having three or four strands can also be designed to exhibit rotational resistant properties.

3.17.6 *Stranded Rope Types:*

3.17.6.1 *compacted strand rope, n*—rope in which the strands, prior to closing of the rope, are subjected to a compacting process such as drawing, rolling, or swaging.

3.17.6.2 *multi-layer, adj*—describes an assembly of two or more layers of strands laid helically around a core, the direction of the lay of the outer strands being opposite (that is, contra-lay) to that of the underlying layer.

3.17.6.3 *single layer, adj*—describes rope consisting of one layer of strands laid helically around a core.

3.17.6.4 *swaged (compacted) rope, n*—rope that is subjected to a compacting process after closing the rope, thus reducing its diameter.

Values

3.18 *actual (measured) value, n*—value derived from direct measurement in a prescribed manner.

3.19 *maximum value, n*—specified value that an actual value must not exceed.

3.20 *minimum value, n*—specified value that an actual value must meet or exceed.

3.21 *nominal value, n*—the conventional value by which a physical characteristic is designated.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

Item	Examples	
	inch-pound	[SI]
Length	500 ft	175 m
Size (diameter)	3/4 in.	16 mm
Rope classification or construction (if known)	6×36	6×36
Preformed or non-preformed	Preformed	Preformed
Lay direction and type	Right regular	sZ
Wire finish (uncoated or metallic coated and type)	uncoated	drawn-galvanized
Rope Grade	EIP	1960
Core Type	FC (fiber)	SC
Applicable specification	ASTM A1023	ASTM A1023
Special requirements		
Termination of rope ends		
Special length tolerance		
Type of certificate		
Special packaging and identification		
Lubrication, other than as noted in 4.3		
Prestretching		

4.2 *Certification of Conformance and Test:*

4.2.1 A certificate of conformance and test shall confirm compliance with this standard. It shall contain the following information items:

4.2.1.1 Certificate number,

4.2.1.2 Purchaser's name and address,

4.2.1.3 Purchaser's order number,

4.2.1.4 Rope supplier's name and address,

4.2.1.5 Supplier's order number,

4.2.1.6 Number traceable to manufacturer's production length,

4.2.1.7 Nominal length(s) of rope,

4.2.1.8 Rope designation (nominal diameter, construction and core, lay and grade), and

4.2.1.9 Minimum breaking force in tons (short tons) or kilonewtons.

4.2.2 *Tests on Wires and Rope*—If wire tests are required, indicate if the wire samples are taken before the rope fabrication or if they are taken from a completed rope. The following additional information can be supplied under agreement between purchaser and supplier. These items shall be completed as agreed between the supplier and the purchaser.

4.2.2.1 Quality system registration number of the rope manufacturer, if applicable;

4.2.2.2 Approximate mass in lb/ft [kg/m];

4.2.2.3 Wire standard used;

4.2.2.4 Number of wires tested;

4.2.2.5 Nominal dimensions of wire;

4.2.2.6 Measured dimensions of wire;

4.2.2.7 Breaking force of wire;

4.2.2.8 Tensile strength of wire;

4.2.2.9 Number of torsions completed (and test length);

4.2.2.10 Mass of zinc (or zinc alloy);

4.2.2.11 Actual (measured) diameter of rope; and

4.2.2.12 Actual (measured) breaking force of rope.

4.2.3 *Additional Information and Certification:*

4.2.3.1 Space for additional information, and

4.2.3.2 Space for certification with provision for certifying the foregoing, name and position held, signature, and date.

5. Material

5.1 *Wire*—The wires used in rope making shall comply with the appropriate requirements of Specification **A1007** or **ISO 2232**. The manufacturer, subject to the limits in **Table 1**, shall determine the tensile strength grade so that the minimum breaking force of the rope is achieved.

5.1.1 Wire tensile limitations in **Table 1** do not apply to center, filler, and core wires.

5.1.2 Wire tensile limitations do not apply to compacted ropes, or compacted strand ropes.

5.1.3 The manufacturer shall have the option to adopt a single wire level or tensile strength grade throughout the rope, or decide on a combination of wire levels or tensile strength grades.

5.1.4 Wire diameters shall be selected by the manufacturer in accordance with applicable wire rope design requirements.

5.2 *Core*—Cores of stranded ropes shall normally be either steel or fiber composition.

5.2.1 *Fiber Core*—All fiber cores shall be natural fiber (for example, sisal), polypropylene, or other suitable synthetic fiber.

The cores shall be of uniform hardness, effectively supporting the strands. Natural fiber cores shall be treated with an impregnating compound free from acid. Fiber cores larger than $\frac{5}{32}$ -in. (4-mm) diameter shall be doubly closed.

5.2.2 *Steel Core*—Steel main cores shall be either an independent wire rope (IWRC) or a wire strand (WSC). Steel cores of single layer ropes larger than $\frac{7}{16}$ -in. (12-mm) diameter shall be independent wire ropes (IWRC), unless specified otherwise. Steel cores shall be lubricated. Cores closed in one operation (parallel lay) with the outer strands of the rope may be specified by agreement between the supplier and the purchaser.

5.3 *Lubricant*—All wire rope, unless otherwise specified, shall be lubricated and impregnated in the manufacturing process with a suitable lubricant selected by the manufacturer. Stranding lubricants used for fiber core ropes shall be compatible with the impregnating compound of the fiber core.

6. Rope Properties and Tolerances

6.1 *Classification*—The rope classification shall be specified by the purchaser and shall normally be one of those covered in **Table 2** although other classifications and constructions are available by agreement between the supplier and purchaser.

NOTE 2—Where only the rope classification is specified by the purchaser, the manufacturer shall determine the construction.

6.2 *Rope Core*—Steel core (SC) shall be supplied unless otherwise specified. The manufacturer shall determine core construction. Cores with inserts or solid polymer cores are subject to agreement between the supplier and purchaser.

6.3 *Rope Grade*—The rope grade shall be one of the following although other grades are available by agreement between the supplier and purchaser.

6.3.1 The listed rope grades for the following inch-pound units are shown in the indicated tables:

6.3.1.1 *IPS*—Tables 10–21, Tables 24–27

6.3.1.2 *EIP*—Tables 10–21, Tables 26–33

6.3.1.3 *EEIP*—Tables 12–20, Tables 26–29, Tables 32 and 33

6.3.2 Rope Grades for the following SI units are shown in the indicated tables:

6.3.2.1 *1770*—Table 10–19, Tables 21–23

6.3.2.2 *1960*—Tables 10–19, Tables 21–23, Tables 28 and 29, Tables 32–34

6.3.2.3 *2160*—Tables 12–19, Table 23, Tables 28 and 29, Tables 32–34

6.4 *Wire Finish*—Unless otherwise specified, wire ropes will be furnished with uncoated wires. For wire ropes requested with metallic coated wires, the wires shall be galvanized unless otherwise specified by the purchaser.

6.4.1 *Final-Galvanized Rope*—All outer wires shall be supplied as final-galvanized. Inner, filler, and center wires shall be supplied as final-galvanized or drawn-galvanized. Minimum weight of coating for galvanized wire shall be as specified in **Tables 3 and 4**.

6.4.1.1 Final-galvanized rope shall be supplied with minimum breaking forces 10 % lower than those listed in Tables 9–34, except for Table 21 and Table 22.

6.4.1.2 *Final-Coated Zn-5Al-MM*—Wires of final-coated Zn-5Al-MM may be substituted for final-galvanized wire at the option of the manufacturer. Minimum weight of coating shall be as specified in **Table 3**.

6.4.2 *Drawn-Galvanized (Zinc Coated) Rope*—All the wires shall be galvanized (zinc coated), including those of any steel core. Minimum weight of coating shall be as specified in **Table 4**.

6.4.2.1 Drawn galvanized rope shall be supplied with minimum breaking forces no less than those listed in Tables 9–34.

6.4.2.2 *Drawn-Zn-5Al-MM*—Wires of drawn-Zn-5Al-MM may be substituted for drawn-galvanized wire at the option of the manufacturer. Minimum weight of coating shall be as specified in **Table 4**.

6.5 *Direction and Type of Rope Lay*—The direction and type of rope lay shall be as specified by the purchaser and shall be one of the following:

Right regular (ordinary) lay (sZ)
Left regular (ordinary) lay (zS)
Right lang lay (zZ)
Left lang lay (sS)
Right alternate lay (AZ)
Left alternate lay (AS)

Right regular (ordinary) lay will be supplied for six, seven, and eight-strand constructions unless otherwise specified by the purchaser.

6.6 *Dimensions*:

6.6.1 *Rope Diameter*—The nominal diameter shall be as specified by the purchaser and shall be the dimension by which the rope is designated.

6.6.1.1 *Tolerance on Rope Diameter*—When measured in accordance with **8.6.1**, the actual diameter shall not vary from the nominal diameter by more than the tolerances specified in **Table 5** or **Table 6**. For small diameter specialty cord with diameters from $\frac{1}{32}$ in. [0.8 mm] to $\frac{3}{8}$ in. [10 mm] inclusive, diameter tolerances shall be as specified in **Table 9**.

6.6.1.2 *Permissible Differences in Diameter*—The difference between any two of the four measurements taken in accordance with **8.6.1**, and expressed as a percentage of the nominal diameter, shall not exceed the values given in **Table 7** or **Table 8**.

6.6.2 *Lay Length*:

6.6.2.1 For single layer ropes of 6×7 class, the lay length of the finish rope shall not exceed 8 times the nominal rope diameter.



6.6.2.2 For other single layer ropes with round strands, except for 3 or 4 strand ropes, and multi-layer ropes with round or shaped strands, the length of lay of the finished rope shall not exceed 7.25 times the nominal rope diameter.

6.6.2.3 For single layer ropes with shaped strands, for example, flattened (triangular) strand, the length of lay of the finished rope shall not exceed 10 times the nominal rope diameter.

6.7 *Mechanical Properties*:

6.7.1 *Breaking Force*—Values for minimum breaking force for the more common classes of rope are specified in Tables 9–34 of this standard.

TABLE 9 Classification 7×7 and 7×19 Small Diameter (Galvanized) Specialty Cord

Cross Section Examples		Construction of Rope		Construction of Strand							
		Item	Quantity	Item	Quantity						
	Strands ^A		7	Wires	7 or 19						
	Outer Strands		6	Outer Wires	6 or 12						
	Layer of Strands		2	Layer of Wires	1 or 2						
	Wires in Rope ^A (excluding core strand)		42 or 114								
		Typical Examples		Number of Outer Wires							
		Rope	Strand	Total	Per Strand						
		3×7	1–6	18	6						
		7×7	1–6	36	6						
		7×19	1–6/12	72	12						
Diameter		Approx. Mass				Minimum Breaking Force ^A				Diameter Range	
in.	[mm]	7×7		7×19		7×7		7×19		Min. in.	Max. in.
		lb/100 ft	[kg/30.5 m]	lb/100 ft	[kg/30.5 m]	lbs	[kN]	lbs	[kN]		
1/32 ^A	0.79	0.16	0.07			110	0.49			0.031	0.037
3/64	1.19	0.42	0.19			270	1.2			0.047	0.055
1/16	1.59	0.75	0.34	0.75	0.34	480	2.1	480	2.1	0.063	0.073
5/64	1.98	1.1	0.50			650	2.9			0.078	0.089
3/32	2.38	1.6	0.73	1.7	0.77	920	4.1	1000	4.4	0.094	0.106
7/64	2.78	2.2	1.0			1260	5.6			0.109	0.122
1/8	3.18	2.8	1.3	2.9	1.3	1700	7.6	2000	8.9	0.125	0.139
5/32	3.97	4.3	2.0	4.5	2.0	2600	11.6	2800	12.5	0.156	0.172
3/16	4.76	6.2	2.8	6.5	3.0	3700	16.5	4200	18.7	0.188	0.206
7/32	5.56	8.3	3.8	8.6	3.9	4800	21.4	5600	24.9	0.219	0.237
1/4	6.35	10.6	4.8	11.0	5.0	6100	27.1	7000	31.1	0.250	0.268
9/32	7.14	13.4	6.1	13.9	6.3	7600	33.8	8000	35.6	0.281	0.301
5/16	7.94	16.7	7.6	17.3	7.9	9200	40.9	9800	43.6	0.313	0.335
11/32	8.73	20.1	9.1	20.7	9.4	11 100	49.4	12 500	55.6	0.344	0.368
3/8	9.53	23.6	10.7	24.3	11.0	13 100	58.3	14 400	64.1	0.375	0.401

^A 1/32 construction is 3×7.

6.7.1.1 The minimum breaking force for other classes and constructions not covered by the tables, shall be agreed upon by the manufacturer and the purchaser.

6.7.1.2 Wire ropes with minimum breaking forces less than those allowed in this specification may be accepted by prior agreement between the supplier and purchaser and shall be regarded as beyond the scope of this specification.

6.7.2 *Mass*—The (approximate) nominal rope mass shall be as given in Tables 9–34 or as specified by the manufacturer.

6.7.3 *Length*—The actual length of rope supplied, expressed in feet or meters, shall be the specified length subject to the following limits of tolerance:

(a) Up to and including 1300 ft [400 m]: +5.0 % of specified length,

(b) Over 1300 ft up to 3280 ft [400 m to 1000 m]: +66 ft [20 m], and

(c) Over 3280 ft [1000 m]: +2.0 % of specified length.

NOTE 3—The rope shall be measured under no load. Ropes required with more restrictive length tolerance shall be agreed upon by the supplier and purchaser.

7. Rope Workmanship and Finish

7.1 Strand:

7.1.1 Strand wires shall be tight and uniform. All the wire layers in a strand shall have the same direction of lay. The lay lengths of corresponding wire layers in strands of the same size shall be uniform.

7.1.2 Center wires and fiber centers of strands shall be of a size to provide sufficient support to enable the covering wires to be evenly laid.

7.2 *Rope*—The rope shall be uniformly made and the strands shall lie tightly on the core or the underlying strands.

7.2.1 The core of a stranded rope, except for swaged (compacted) ropes, shall be designed so that in a new rope under no load there is clearance between the outer strands.

7.2.2 Rope ends that have no end fittings shall be so secured as to maintain the integrity of the rope and prevent its unraveling.

7.3 Wire Joints:

7.3.1 Wires over 0.015 in. [0.4 mm] in diameter shall have their ends joined by soldering, brazing, or welding.

7.3.2 Wires up to and including 0.015 in. [0.4 mm] diameter may be joined by soldering, brazing, welding, twisting, or by ends being simply inserted into the strand's formation.

7.3.3 The minimum distance between joints in a strand shall be 18 times the nominal rope diameter.

7.4 *Preformation*—Stranded ropes shall be preformed unless otherwise specified, except that multi-layer ropes, including rotation-resistant and low-rotation ropes, may be non-preformed.

7.5 *Prestretching*—Stranded ropes are not prestretched unless otherwise specified. When specified, ropes may be prestretched using either a process of static or dynamic loading. Prestretch loads shall not exceed 55 % of the minimum breaking force for the rope.

NOTE 4—Example of static prestretching practice: Rope is subjected to three cycles of tensile loading to 40 % of the ropes minimum breaking

force for 5 min, returning to 5 % of the minimum breaking force between cycles. After the last cycle, the tensile load is completely released.

8. Testing and Compliance

General

8.1 Wire ropes manufactured in accordance with this specification shall be capable of meeting all the appropriate requirements as specified in 8.2. The manufacturer shall be able to demonstrate compliance with this specification by either:

8.1.1 Testing each production length in accordance with 8.2, or

8.1.2 Operating a quality assurance system that includes a sampling program that meets the following requirements as a minimum:

8.1.2.1 For each size and grade of a given rope construction, the manufacturer shall present evidence from testing, if requested by the purchaser, of a minimum of three production lengths representing the current design. The purpose of these tests is to assure the manufacturer's ability to produce a rope that conforms to the minimum requirements as defined in this specification. Periodic acceptance tests are successfully completed on a sample taken from a minimum of every twentieth production length.

8.1.2.2 Manufacturers complying with all requirements of 8.1.2 may use calculated breaking force to verify compliance with requirements for an individual production length not included in sample testing.

8.2 Any change in design requires that the tests specified in 8.1.2 be repeated on the modified rope. However, if the same design, apart from the wire tensile grades, is used for ropes of a lower grade than the one which has successfully passed the tests specified in 8.1.2, it shall not be necessary to repeat the tests on the lower grade rope(s).

8.3 For the purposes of this specification, a production length is regarded as that length of rope manufactured in one continuous operation from one loading of the closing machine comprising strands, each of which has been produced in one continuous operation on the stranding machine. A production length may comprise one or more reels of rope.

NOTE 5—Examples of quality assurance systems are API Q1, ANSI/ASQC Q9002 and ISO 9002.

Acceptance Tests

8.4 *Test Piece*—When required by 8.1, one test piece shall be taken from each production length.

8.5 *Test Verification*—When requested, the manufacturer shall allow the purchaser or his representative the opportunity to witness acceptance tests (when these are performed), or to examine test records, to verify compliance with this specification. Test lengths required by the purchaser should be ordered as additional lengths.

8.6 Rope:

8.6.1 *Diameter*—Measurements for diameter shall be taken on a straight portion of the rope without tension, at two positions spaced at least three feet (or one meter) apart, and at each position two diameters at right angles shall be measured. The average of these four measurements shall be within the tolerances given in Tables 5 and 6 of this specification. The

permissible differences between any two individual diameter measurements are given in **Tables 7 and 8**.

NOTE 6—In case of dispute concerning oversize diameter, the rope shall be measured under a tension not exceeding 20 % of the minimum breaking force. If the measurements from this test are within the specified tolerances, the rope shall be deemed to be within the specified size.

8.6.2 Breaking Force—When measured in accordance with the method specified in Test Method **A931** or **ISO 3108**, the actual (measured) breaking force obtained shall be equal to or greater than the minimum breaking force required by this specification. If the minimum breaking force is not achieved, up to three additional tests shall be permitted. At least one of the additional tests shall achieve the minimum breaking force specified. Tables 9–34 show the minimum breaking forces of the more common classes, sizes, and grades of ropes:

8.6.2.1 Minimum breaking forces listed apply to uncoated or drawn-galvanized ropes.

8.6.2.2 Minimum breaking forces for final-galvanized ropes are 10 % lower than values listed, except for Tables 21 and 22.

8.6.2.3 Minimum breaking force values for IPS, EIP and EEIP are given in short tons of 2000 pounds.

8.7 Rope Wires:

8.7.1 General—Wires shall be tested for diameter, tensile strength, torsions, and, where applicable, metallic coating in accordance with the methods in Specification **A1007** or **ISO 2232**. The manufacturer shall have the option to test wires either before or after fabrication of the rope.

NOTE 7—After fabrication wire testing is not applicable to compacted strand ropes or swaged (compacted) ropes.

8.7.2 Sampling—All main wires from the equivalent of one complete strand of each layer, strand diameter and strand construction, including steel rope core, shall be tested. If there are more than eight strands of one diameter in one layer, then two strands of that diameter shall be tested.

8.7.3 For the purpose of evaluating the test results, the rope manufacturer shall record the nominal diameters and tensile grades of the wires.

8.7.3.1 The sample selected shall be of sufficient length to allow for retest.

8.7.3.2 The wires shall be selected at random.

8.7.3.3 Filler wires and center wires shall be excluded from this test.

8.7.4 Levels of Acceptance:

8.7.4.1 Wire before Fabrication—Wire samples tested before fabrication shall meet the requirements for the size and grade (level) specified by the supplier and as found in the appropriate wire specification.

8.7.4.2 Wire after Fabrication—For each requirement, a maximum of 5 % of wires tested is permitted to lie outside the values specified, rounded to the nearest whole number of wires. Failure of the same wire to satisfy more than one requirement shall be considered as a single failure.

(a) **Diameter**—The diameter of 5 % of the wires may exceed, by up to 50 %, the specified tolerance for the nominal diameter.

(b) **Tensile Strength**—When tested in accordance with the requirements of Specification **A1007**, the measured values shall be within the tolerance specified with an additional tolerance of 7000 psi [50 N/mm²] below the minimum value. The measured value of wire diameters less than 0.020 in. [0.5 mm] shall be greater than the minimum values specified in the appropriate wire specification.

(c) **Torsion**—When tested in accordance with the requirements of Specification **A1007**, the measured values of wires of 0.020 in. [0.5 mm] diameter and greater shall be at least 85 % of the values specified, rounded down to the next whole number. The measured value of wire diameters less than 0.020 in. [0.5 mm] shall be greater than the minimum values specified.

9. Packaging and Identification

9.1 Packaging—Unless otherwise specified by the purchaser, ropes shall be supplied in coils or on reels at the discretion of the manufacturer.

9.2 Identification—Each package of rope shall be legibly identified with the following information, as a minimum:

9.2.1 Rope supplier and address,


9.2.2 Rope length and description, and

9.2.3 Number traceable to manufacturer's production length.

10. Keywords

10.1 aircraft cable; cable; steel cable; steel rope; utility cable; wire rope


TABLE 10 Classification 6×7 Steel Core

Cross Section Examples		Construction of Rope				Construction of Strand			
		Item		Quantity		Item		Quantity	
		Strands		6		Wires		5 to 9	
		Outer Strands		6		Outer Wires		4 to 8	
		Layer of Strands		1		Layer of Wires		1	
		Wires in Rope		30 to 54					
		Typical Examples				Number of Outer Wires			
6×7 SC		Rope 6×7		Strand 1–6		Total 36		Per Strand 6	
Diameter		Approx. Mass		Minimum Breaking Force ⁴				Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS	1770	EIP	1960	Min.	Max.
				Tons	[kN]	Tons	[kN]	in.	in.
1/4	6	0.10	0.144		22.9		25.3	0.236	0.250
		0.11	0.161	2.84		3.12		0.250	0.265
	7	0.13	0.196		31.1		34.5	0.276	0.292
5/16		0.17	0.252	4.41		4.85		0.313	0.331
	8	0.17	0.256		40.7		45.0	0.315	0.331
	9	0.22	0.324		51.5		57.0	0.354	0.372
3/8		0.24	0.363	6.30		6.93		0.375	0.394
	10	0.27	0.400		63.5		70.4	0.394	0.413
	11	0.33	0.484		76.9		85.1	0.433	0.455
7/16		0.33	0.494	8.52		9.37		0.438	0.459
	12	0.39	0.576		91.5		101	0.472	0.496
1/2		0.43	0.645	11.1		12.2		0.500	0.525
	13	0.45	0.676		107		119	0.512	0.537
	14	0.53	0.784		125		138	0.551	0.579
9/16		0.55	0.817	14.0		15.4		0.563	0.591
5/8		0.68	1.008	17.1		18.8		0.625	0.656
	16	0.69	1.024		163		180	0.630	0.661
	18	0.87	1.296		206		228	0.709	0.744
	19	0.97	1.444		229		254	0.748	0.785
3/4		0.98	1.452	24.4		26.8		0.750	0.788
	20	1.08	1.600		254		281	0.787	0.827
	22	1.30	1.936		308		341	0.866	0.909
7/8		1.33	1.976	33.0		36.3		0.875	0.919
	24	1.55	2.304		366		405	0.945	0.992
1		1.73	2.581	42.7		47.0		1.000	1.050
	26	1.82	2.704		430		476	1.024	1.075
	28	2.11	3.136		498		552	1.102	1.157
1 1/8		2.19	3.266	53.5		58.9		1.125	1.181
1 1/4		2.71	4.032	65.6		72.2		1.250	1.313
	32	2.75	4.096		651		721	1.260	1.323
1 3/8		3.28	4.879	78.6		86.5		1.375	1.444
	36	3.48	5.184		824		912	1.417	1.488
1 1/2		3.90	5.806	92.7		102		1.500	1.575

⁴ Minimum breaking force for final-galvanized ropes 10 % lower than values listed.



Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 11 Classification 6×7 Fiber Core

Cross Section Examples		Construction of Rope				Construction of Strand			
		Item		Quantity		Item		Quantity	
		Strands		6		Wires		5 to 9	
		Outer Strands		6		Outer Wires		4 to 8	
		Layer of Strands		1		Layer of Wires		1	
		Wires in Rope		30 to 54					
		Typical Examples				Number of Outer Wires			
		Rope		Strand		Total	Per Strand		
		6×7		1–6		36	6		
Diameter		Approx. Mass		Minimum Breaking Force ^A				Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS	1770	EIP	1960	Min.	Max.
				Tons	[kN]	Tons	[kN]	in.	in.
	6	0.08	0.124		21.2		23.4	0.236	0.248
1/4	7	0.09	0.139	2.64	28.8	2.90	31.9	0.250	0.263
		0.11	0.169					0.276	0.289
5/16	8	0.15	0.217	4.10	37.6	4.51	41.6	0.313	0.328
		0.15	0.221		47.6		52.7	0.315	0.331
	9	0.19	0.279					0.354	0.372
3/8	10	0.21	0.313	5.86	58.8	6.45	65.1	0.375	0.394
		0.23	0.345		71.1		78.7	0.394	0.413
	11	0.28	0.417					0.433	0.455
7/16	12	0.29	0.426	7.93	84.6	8.72	93.7	0.438	0.459
		0.33	0.497					0.472	0.496
1/2	13	0.37	0.556	10.3	99.3	11.3	110	0.500	0.525
		0.39	0.583		115		128	0.512	0.537
	14	0.45	0.676					0.551	0.579
9/16	15	0.47	0.704	13.0		14.3		0.563	0.591
5/8	16	0.58	0.869	15.9	150		167	0.625	0.656
		0.59	0.883		190		211	0.630	0.661
	18	0.75	1.118		212		235	0.709	0.744
		0.84	1.245					0.748	0.785
3/4	19	0.84	1.252	22.7	235	25.0	260	0.750	0.788
		0.93	1.380		284		315	0.787	0.827
	20	1.12	1.670					0.866	0.909
7/8	22	1.15	1.704	30.7	338	33.8	375	0.875	0.919
		1.34	1.987					0.945	0.992
1	24	1.50	2.226	39.7	397	43.7	440	1.000	1.050
		1.57	2.332		461		510	1.024	1.075
	26	1.82	2.705					1.102	1.157
1 1/8	28	1.89	2.817	49.8		54.8		1.125	1.181
1 1/4	30	2.34	3.478	61.0	602	67.1	666	1.250	1.313
		2.37	3.533					1.260	1.323
1 3/8	32	2.83	4.208	73.1		80.4		1.375	1.444
		3.00	4.471		762		843	1.417	1.488
1 1/2	36	3.37	5.008	86.2		94.8		1.500	1.575

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.
 Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 12 Classification 6×19 Steel Core

Cross Section Examples	Construction of Rope		Construction of Strand	
	Item	Quantity	Item	Quantity
 <p>6×19 Seale IWRC</p>	Strands	6	Wires	15 to 26
	Outer Strands	6	Outer Wires	7 to 12
	Layer of Strands	1	Layer of Wires	2 to 3
	Wires in Rope	90 to 156		
 <p>6×25 filler wire IWRC</p>	Typical Examples		Number of Outer Wires	
	Rope	Strand	Total	Per Strand
	6×19S	1-9-9	54	9
	6×21F	1-5-5F-10	60	10
	6×26WS	1-5-(5+5)-10	60	10
6×19W	1-6-(6+6)	72	12	
6×25F	1-6-6F-12	72	12	

Diameter	Approx. Mass	Minimum Breaking Force ^A				Diameter Range					
		IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.		
1/4	6	0.10	0.153		22.7		25.1		27.7	0.236	0.250
		0.12	0.172	2.94		3.40				0.250	0.265
5/16	7	0.14	0.209		30.9		34.2		37.7	0.276	0.292
		0.18	0.268	4.58		5.27				0.313	0.331
3/8	8	0.18	0.273		40.3		44.7		49.2	0.315	0.331
		0.23	0.345		51.0		56.5		62.3	0.354	0.372
7/16	9	0.26	0.386	6.56		7.55		8.30		0.375	0.394
		0.29	0.426		63.0		69.8		76.9	0.394	0.413
1/2	11	0.35	0.515		76.2		84.4		93.0	0.433	0.455
		0.35	0.526	8.89		10.2			11.2	0.438	0.459
5/8	12	0.41	0.613		90.7		100		111	0.472	0.496
		0.46	0.687	11.5		13.3		14.6		0.500	0.525
3/4	13	0.48	0.720		106		118		130	0.512	0.537
		0.56	0.835		124		137		151	0.551	0.579
7/8	14	0.58	0.870	14.5		16.8		18.5		0.563	0.591
		0.72	1.074	17.7		20.6		22.7		0.625	0.656
1	16	0.73	1.091		161		179		197	0.630	0.661
		0.93	1.380		204		226		249	0.709	0.744
1 1/8	18	1.03	1.538		227		252		278	0.748	0.785
		1.04	1.546	25.6		29.4		32.4		0.750	0.788
1 1/4	20	1.15	1.704		252		279		308	0.787	0.827
		1.39	2.062		305		338		372	0.866	0.909
1 1/2	22	1.41	2.104	34.6		39.8		43.8		0.875	0.919
		1.65	2.454		363		402		443	0.945	0.992
1 3/8	24	1.85	2.748	44.9		51.7		56.9		1.000	1.050
		1.94	2.880		426		472		520	1.024	1.075
1 3/4	26	2.24	3.340		494		547		603	1.102	1.157
		2.34	3.478	56.5		65.0		71.5		1.125	1.181
1 7/8	28	2.89	4.294	69.4		79.9		87.9		1.250	1.313
		2.93	4.362		645		715		787	1.260	1.323
2	32	3.49	5.196	83.5		96.0		106		1.375	1.444
		3.71	5.521		817		904		997	1.417	1.488
2 1/8	36	4.16	6.184	98.9		114		125		1.500	1.575
		4.58	6.816		1008		1116		1230	1.575	1.654
2 1/4	40	4.88	7.257	115		132		146		1.625	1.706
		5.54	8.247		1220		1351		1489	1.732	1.819
2 3/8	44	5.66	8.417	133		153		169		1.750	1.838
		6.49	9.662	152		174		192		1.875	1.969
2 1/2	48	6.60	9.815		1452		1608		1772	1.890	1.984
		7.39	10.994	172		198		217		2.000	2.100
2 5/8	52	7.74	11.519		1704		1887		2079	2.047	2.150
		8.34	12.411	192		221		243		2.125	2.231
3	56	8.98	13.359		1976		2188		2411	2.205	2.315
		9.35	13.914	215		247		272		2.250	2.363
3 1/4	60	10.31	15.336		2268		2512		2768	2.362	2.480
		10.42	15.503	239		274		301		2.375	2.494
3 1/2		11.6	17.261	262		302		332		2.500	2.625



TABLE 12 *Continued*

Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
2 ⁵ / ₈		12.8	19.046	288		331		364		2.625	2.756
2 ³ / ₄		14.0	20.832	314		361		397		2.750	2.888
2 ⁷ / ₈		15.3	22.766	341		392		432		2.875	3.019
3		16.6	24.701	370		425		438		3.000	3.150
3 ¹ / ₈		18.1	26.933	399		458		504		3.125	3.281
3 ¹ / ₄		19.5	29.016	429		492		543		3.250	3.413
3 ³ / ₈		21.0	31.248	459		529		582		3.375	3.544
3 ¹ / ₂		22.7	33.778	491		564		621		3.500	3.675

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 13 Classification 6×19 Fiber Core

Cross Section Examples	Construction of Rope		Construction of Strand		
	Item	Quantity	Item	Quantity	
 6×21 fiber wire FC	Strands	6	Wires	15 to 26	
	Outer Strands	6	Outer Wires	7 to 12	
	Layer of Strands	1	Layer of Wires	2 to 3	
	Wires in Rope	90 to 156			
 6×25 fiber wire FC	Typical Examples		Number of Outer Wires		
		Rope	Strand	Total	Per Strand
		6×19S	1–9–9	54	9
		6×21F	1–5–5F–10	60	10
		6×26WS	1–5–(5+5)–10	60	10
	6×19W	1–6–(6+6)	72	12	
	6×25F	1–6–6F–12	72	12	

Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
1/4	6	0.09	0.140		21.0		23.3		25.7	0.236	0.250
		0.11	0.156	2.74		3.01				0.250	0.265
	7	0.13	0.190		28.6		31.7		34.9	0.276	0.292
5/16		0.16	0.244	4.26		4.69				0.313	0.331
	8	0.17	0.248		37.4		41.4		45.6	0.315	0.331
	9	0.21	0.314		47.3		52.4		57.7	0.354	0.372
3/8		0.24	0.352	6.10		6.71		7.38		0.375	0.394
	10	0.26	0.388		58.4		64.7		71.3	0.394	0.413
	11	0.32	0.469		70.7		78.3		86.2	0.433	0.455
7/16		0.32	0.479	8.27		9.10		10.0		0.438	0.459
	12	0.38	0.559		84.1		93.1		103	0.472	0.496
1/2		0.42	0.626	10.7		11.8		12.9		0.500	0.525
	13	0.44	0.656		98.7		109		120	0.512	0.537
	14	0.51	0.760		114		127		140	0.551	0.579
9/16		0.53	0.792	13.5		14.9		16.3		0.563	0.591
5/8		0.66	0.978	16.7		18.4		20.2		0.625	0.656
	16	0.67	0.993		150		166		182	0.630	0.661
	18	0.84	1.257		189		210		231	0.709	0.744
	19	0.94	1.401		211		233		257	0.748	0.785
3/4		0.95	1.408	23.8		26.2		28.8		0.750	0.788
	20	1.04	1.552		234		259		285	0.787	0.827
	22	1.26	1.878		283		313		345	0.866	0.909
7/8		1.29	1.917	32.2		35.4		39.0		0.875	0.919
	24	1.50	2.235		336		373		411	0.945	0.992
1		1.68	2.503	41.8		46.0		50.6		1.000	1.050
	26	1.76	2.623		395		437		482	1.024	1.075
	28	2.04	3.042		458		507		559	1.102	1.157
1 1/8		2.13	3.168	52.6		57.9		63.6		1.125	1.181
1 1/4		2.63	3.911	64.6		71.1		78.2		1.250	1.313
	32	2.67	3.973		598		662		730	1.260	1.323
1 3/8		3.18	4.733	77.7		85.5		94.0		1.375	1.444
	36	3.38	5.028		757		838		924	1.417	1.488
1 1/2		3.78	5.632	92.0		101		111		1.500	1.575
	40	4.17	6.208		935		1035		1140	1.575	1.654
1 5/8		4.44	6.610	107		118		129		1.625	1.706
	44	5.05	7.512		1131		1252		1380	1.732	1.819
1 3/4		5.15	7.666	124		136		150		1.750	1.838
1 7/8		5.91	8.800	141		155		171		1.875	1.969
	48	6.01	8.940		1346		1490		1642	1.890	1.984
2		6.73	10.013	160		176		194		2.000	2.100
	52	7.05	10.492		1579		1749		1927	2.047	2.150
2 1/8		7.60	11.304	179		197		217		2.125	2.231
	56	8.18	12.168		1832		2028		2235	2.205	2.315
2 1/4		8.52	12.673	200		220		242		2.250	2.363



TABLE 13 *Continued*

Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
	60	9.39	13.968		2103		2328		2566	2.362	2.480
2 ³ / ₈		9.49	14.120	222		244		269		2.375	2.494
2 ¹ / ₂		10.5	15.624	244		269		295		2.500	2.625
2 ⁵ / ₈		11.6	17.261	268		294		324		2.625	2.756
2 ³ / ₄		12.7	18.898	292		321		353		2.750	2.888
2 ⁷ / ₈		13.9	20.683	317		349		384		2.875	3.019
3		15.1	22.469	344		378		416		3.000	3.150
3 ¹ / ₈		16.4	24.403	371		408		448		3.125	3.281
3 ¹ / ₄		17.7	26.338	399		438		483		3.250	3.413
3 ³ / ₈		19.1	28.421	427		470		518		3.375	3.544
3 ¹ / ₂		20.6	30.653	457		503		552		3.500	3.675

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 14 Classification 6×36 Steel Core

Cross Section Examples	Construction of Rope		Construction of Strand	
	Item	Quantity	Item	Quantity
 6×31 Warrington Seale IWRC	Strands	6	Wires	27 to 49
	Outer Strands	6	Outer Wires	12 to 18
	Layer of Strands	1	Layer of Wires	3 to 4
	Wires in Rope (excluding steel core)	156 to 276		
 6×41 Warrington Seale IWRC	Typical Examples		Number of Outer Wires	
	Rope	Strand	Total	Per Strand
	6×31WS	1–6–(6+6)–12	72	12
	6×36WS	1–7–(7+7)–14	84	14
	6×41WS	1–8–(8+8)–16	96	16
	6×41SF	1–8–8–8F–16	96	16
	6×49SWS	1–8–8–(8+8)–16	96	16
6×46WS	1–9–(9+9)–18	108	18	

Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
1/4	6	0.10	0.153	2.94	22.7	3.40	25.1		27.7	0.236	0.250
			0.12		0.172					0.250	0.265
5/16	7	0.14	0.209	4.58	30.9	5.27	34.2		37.7	0.276	0.292
			0.18		0.268					0.313	0.331
3/8	8	0.18	0.273	6.56	40.3	7.55	44.7	8.30	49.2	0.315	0.331
			0.23		0.345					56.5	62.3
7/16	9	0.26	0.386	8.89	63.0	10.2	69.8	11.2	76.9	0.375	0.394
			0.426		51.0					84.4	93.0
1/2	10	0.35	0.515	11.5	76.2	13.3	84.4	14.6	93.0	0.438	0.459
			0.526		89.7					100	111
9/16	11	0.41	0.613	17.7	90.7	20.6	100	18.5	111	0.500	0.525
			0.687		106					118	130
5/8	12	0.48	0.720	14.5	124	29.4	137	22.7	151	0.551	0.579
			0.835		14.5					16.8	18.5
3/4	13	0.56	0.870	25.6	17.7	39.8	20.6	32.4	22.7	0.625	0.656
			1.074		161					179	197
7/8	14	0.73	1.091	34.6	204	51.7	226	43.8	249	0.709	0.744
			1.380		227					252	278
1	15	1.03	1.538	44.9	227	65.0	252	56.9	278	0.750	0.788
			1.546		25.6					29.4	32.4
1 1/8	16	1.15	1.704	56.5	252	79.9	279	71.5	308	0.866	0.909
			2.062		305					338	372
1 1/4	17	1.39	2.062	69.4	305	96.0	338	87.9	372	0.875	0.919
			2.104		34.6					39.8	43.8
1 1/2	18	1.41	2.104	83.5	363	114	402	106	443	0.945	0.992
			2.454		44.9					51.7	56.9
1 3/8	19	1.65	2.454	98.9	426	132	472	125	520	1.024	1.075
			2.748		494					472	520
1 3/4	20	1.85	2.748	115	494	153	547	146	603	1.102	1.157
			2.880		56.5					65.0	71.5
1 7/8	21	1.94	2.880	133	56.5	174	547	169	603	1.250	1.313
			3.340		69.4					79.9	87.9
2	22	2.34	3.478	83.5	645	198	715	106	787	1.260	1.323
			4.294		83.5					96.0	106
2 1/8	23	2.89	4.294	98.9	817	221	904	125	997	1.417	1.488
			4.362		98.9					114	125
2 1/4	24	3.49	5.196	115	817	247	904	146	997	1.575	1.654
			5.521		115					132	146
2 3/8	25	3.71	5.521	133	817	279	904	169	997	1.732	1.819
			6.184		133					153	169
2 3/4	26	4.58	6.816	152	1008	298	1116	192	1230	1.875	1.969
			7.257		152					174	192
3	27	4.88	7.257	172	1452	321	1608	217	1772	1.890	1.984
			8.247		172					1608	217
3 1/8	28	5.54	8.247	192	1704	351	1887	243	2079	2.047	2.150
			8.417		192					2188	243
3 1/4	29	5.66	8.417	215	1976	372	2188	272	2411	2.205	2.315
			9.815		215					2188	272


TABLE 14 *Continued*

Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
	60	10.31	15.336		2268		2512		2768	2.362	2.480
2 ³ / ₈		10.42	15.503	239		274		301		2.375	2.494
2 ¹ / ₂		11.6	17.261	262		302		332		2.500	2.625
2 ⁵ / ₈		12.8	19.046	288		331		364		2.625	2.756
2 ³ / ₄		14.0	20.832	314		361		397		2.750	2.888
2 ⁷ / ₈		15.3	22.766	341		392		432		2.875	3.019
3		16.6	24.701	370		425		438		3.000	3.150
3 ¹ / ₈		18.1	26.933	399		458		504		3.125	3.281
3 ¹ / ₄		19.5	29.016	429		492		543		3.250	3.413
3 ³ / ₈		21.0	31.248	459		529		582		3.375	3.544
3 ¹ / ₂		22.7	33.778	491		564		621		3.500	3.675

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 15 Classification 6×36 Fiber Core

Cross Section Examples		Construction of Rope				Construction of Strand					
		Item		Quantity		Item		Quantity			
 <p>6×36 Warrington Seale FC</p>		Strands	6		Wires	27 to 49					
		Outer Strands	6		Outer Wires	12 to 18					
		Layer of Strands	1		Layer of Wires	3 to 4					
		Wires in Rope	156 to 276								
		Typical Examples				Number of Outer Wires					
		Rope	Strand		Total	Per Strand					
		6×31WS	1-6-(6+6)-12		72	12					
		6×36WS	1-7-(7+7)-14		84	14					
		6×41WS	1-8-(8+8)-16		96	16					
		6×41SF	1-8-8-8F-16		96	16					
6×49SWS	1-8-8-(8+8)-16		96	16							
6×46WS	1-9-(9+9)-18		108	18							
Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
1/4	6	0.09	0.140		21.0		23.3		25.7	0.236	0.250
		0.11	0.156	2.74		3.01				0.250	0.265
5/16	7	0.13	0.190		28.6		31.7		34.9	0.276	0.292
		0.16	0.244	4.26		4.69				0.313	0.331
3/8	8	0.17	0.248		37.4		41.4		45.6	0.315	0.331
		0.21	0.314		47.3		52.4		57.7	0.354	0.372
7/16	9	0.24	0.352	6.10		6.71		7.38		0.375	0.394
		0.26	0.388		58.4		64.7		71.3	0.394	0.413
1/2	10	0.32	0.479	8.27		9.10		10.0		0.438	0.459
		0.38	0.559		84.1		93.1		103	0.472	0.496
5/8	11	0.42	0.626	10.7		11.8		12.9		0.500	0.525
		0.44	0.656		98.7		109		120	0.512	0.537
3/4	12	0.51	0.760		114		127		140	0.551	0.579
		0.53	0.792	13.5		14.9		16.3		0.563	0.591
7/8	13	0.66	0.978	16.7		18.4		20.2		0.625	0.656
		0.67	0.993		150		166		182	0.630	0.661
1	14	0.84	1.257		189		210		231	0.709	0.744
		0.94	1.401		211		233		257	0.748	0.785
1 1/8	16	0.95	1.408	23.8		26.2		28.8		0.750	0.788
		1.04	1.552		234		259		285	0.787	0.827
1 1/4	18	1.26	1.878		283		313		345	0.866	0.909
		1.29	1.917	32.2		35.4		39.0		0.875	0.919
1 1/2	19	1.50	2.235		336		373		411	0.945	0.992
		1.68	2.503	41.8		46.0		50.6		1.000	1.050
1 3/8	20	1.76	2.623		395		437		482	1.024	1.075
		2.04	3.042		458		507		559	1.102	1.157
1 3/4	22	2.13	3.168	52.6		57.9		63.6		1.125	1.181
		2.63	3.911	64.6		71.1		78.2		1.250	1.313
1 7/8	24	2.67	3.973		598		662		730	1.260	1.323
		3.18	4.733	77.7		85.5		94.0		1.375	1.444
2	26	3.38	5.028		757		838		924	1.417	1.488
		3.78	5.632	92.0		101		111		1.500	1.575
2 1/8	28	4.17	6.208		935		1035		1140	1.575	1.654
		4.44	6.610	107		118		129		1.625	1.706
2 1/4	32	5.05	7.512		1131		1252		1380	1.732	1.819
		5.15	7.666	124		136		150		1.750	1.838
2 3/8	36	5.91	8.800	141		155		171		1.875	1.969
		6.01	8.940		1346		1490		1642	1.890	1.984
2 3/4	40	6.73	10.013	160		176		194		2.000	2.100
		7.05	10.492		1579		1749		1927	2.047	2.150
2 7/8	44	7.60	11.304	179		197		217		2.125	2.231
		8.18	12.168		1832		2028		2235	2.205	2.315
3	48	8.52	12.673	200		220		242		2.250	2.363
		9.39	13.968		2103		2328		2566	2.362	2.480
3 1/8	52	9.49	14.120	222		244		269		2.375	2.494
		10.5	15.624	244		269		295		2.500	2.625
3 1/4	56	11.6	17.261	268		294		324		2.625	2.756
		12.7	18.898	292		321		353		2.750	2.888
3 3/8	60	13.9	20.683	317		349		384		2.875	3.019
		15.1	22.469	344		378		416		3.000	3.150
3 7/8	64	16.4	24.403	371		408		448		3.125	3.281
		17.7	26.338	399		438		483		3.250	3.413
4	68	19.1	28.421	427		470		518		3.375	3.544
		20.6	30.653	457		503		552		3.500	3.675

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 16 Classification 7×19 Steel Core

Cross Section Examples		Construction of Rope				Construction of Strand						
		Item		Quantity		Item		Quantity				
 <p>7×25 filler wire IWRC</p>		Strands		7		Wires		15 to 26				
		Outer Strands		7		Outer Wires		7 to 12				
		Layer of Strands		1		Layer of Wires		2 to 3				
		Wires in Rope		105 to 182								
		Typical Examples				Number of Outer Wires						
		Rope		Strand		Total		Per Strand				
		7×19S		1-9-9		63		9				
		7×21F		1-5-5F-10		70		10				
		7×26WS		1-5-(5+5)-10		70		10				
		7×19W		1-6-(6+6)		84		12				
		7×25F		1-6-6F-12		84		12				
Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range		
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.	
¼	6	0.11	0.157		22.7		25.1		27.7	0.236	0.250	
		0.12	0.176	2.94		3.40				0.250	0.265	
⅝	7	0.14	0.214		30.9		34.2		37.7	0.276	0.292	
		0.19	0.275	4.58		5.27				0.313	0.331	
¾	8	0.19	0.280		40.3		44.7		49.2	0.315	0.331	
		0.24	0.354		51.0		56.5		62.3	0.354	0.372	
⅞	9	0.27	0.396	6.56		7.55		8.30		0.375	0.394	
		0.29	0.437		63.0		69.8		76.9	0.394	0.413	
1	11	0.36	0.529		76.2		84.4		93.0	0.433	0.455	
		0.42	0.629	8.89		10.2		11.2		111	0.438	0.459
1 ¼	12	0.47	0.705		90.7		100		111	0.472	0.496	
		0.50	0.739	11.5		13.3		14.6		130	0.500	0.525
1 ½	13	0.58	0.857		124		137		151	0.512	0.537	
		0.60	0.892	14.5		16.8		18.5		151	0.551	0.579
1 ⅝	14	0.74	1.101		17.7		20.6		22.7	0.563	0.591	
		0.75	1.119	17.7		20.6		22.7		0.625	0.656	
1 ¾	16	0.95	1.416		161		179		197	0.630	0.661	
		1.06	1.578		204		226		249	0.709	0.744	
2	18	1.07	1.586	25.6		29.4		32.4		278	0.748	0.785
		1.17	1.748		252		279		308	0.750	0.788	
2 ¼	20	1.42	2.115		305		338		372	0.787	0.827	
		1.45	2.159	34.6		39.8		43.8		372	0.866	0.909
2 ½	22	1.69	2.517		363		402		443	0.875	0.919	
		1.89	2.819		426		472		520	0.945	0.992	
2 ¾	24	1.89	2.819	44.9		51.7		56.9		1.000	1.050	
		2.30	3.426		494		547		603	1.024	1.075	
3	26	2.40	3.568		56.5		65.0		71.5	1.102	1.157	
		2.40	3.568	56.5		65.0		71.5		1.125	1.181	
3 ¼	28	2.96	4.405		69.4		79.9		87.9	1.250	1.313	
		3.01	4.475		645		715		787	1.260	1.323	
3 ½	32	3.58	5.330	83.5		96.0		106		1.375	1.444	
		3.81	5.664		817		904		997	1.417	1.488	
3 ¾	36	4.26	6.344		98.9		114		125	1.475	1.544	
		4.70	6.992		1008		1116		1230	1.500	1.575	
4	40	5.00	7.445	115		132		146		1.575	1.654	
		5.69	8.460		1220		1351		1489	1.625	1.706	
4 ¼	44	5.80	8.634		133		153		169	1.732	1.819	
		6.66	9.912		152		174		192	1.750	1.838	
4 ½	48	6.77	10.068		1452		1608		1772	1.875	1.969	
		7.58	11.277	172		198		217		1.890	1.984	
4 ¾	52	7.94	11.816		1704		1887		2079	2.000	2.100	
		8.56	12.731	192		221		243		2.047	2.150	
5	56	9.21	13.704		1976		2188		2411	2.125	2.231	
		9.59	14.273	215		247		272		2.205	2.315	
5 ¼	60	10.57	15.732		2268		2512		2768	2.250	2.363	
		10.69	15.903	239		274		301		2.362	2.480	
										2.375	2.494	

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 17 Classification 7×36 Steel Core



Cross Section Examples		Construction of Rope				Construction of Strand			
		Item	Quantity	Item	Quantity				
 <p>7×36 Warrington Seale IWRC</p>		Strands	7	Wires	27 to 49				
		Outer Strands	7	Outer Wires	12 to 18				
		Layer of Strands	1	Layer of Wires	3 to 4				
		Wires in Rope	189 to 343						
		Typical Examples		Number of Outer Wires					
Rope	Strand	Total	Per Strand						
7×31WS	1-6-(6+6)-12	84	12						
7×36WS	1-7-(7+7)-14	98	14						
7×41WS	1-8-(8+8)-16	112	16						
7×41SF	1-8-8-8F-16	112	16						
7×49SWS	1-8-8-(8+8)-16	112	16						
7×46WS	1-9-(9+9)-18	126	18						

Diameter		Approx. Mass		Minimum Breaking Force ^A						Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
1/4	6	0.11	0.157		22.7		25.1		27.7	0.236	0.250
		0.12	0.176	2.94		3.40				0.250	0.265
	7	0.14	0.214		30.9		34.2		37.7	0.276	0.292
5/16		0.19	0.275	4.58		5.27				0.313	0.331
	8	0.19	0.280		40.3		44.7		49.2	0.315	0.331
	9	0.24	0.354		51.0		56.5		62.3	0.354	0.372
3/8		0.27	0.396	6.56		7.55		8.30		0.375	0.394
	10	0.29	0.437		63.0		69.8		76.9	0.394	0.413
	11	0.36	0.529		76.2		84.4		93.0	0.433	0.455
7/16		0.36	0.540	8.89		10.2		11.2		0.438	0.459
	12	0.42	0.629		90.7		100		111	0.472	0.496
1/2		0.47	0.705	11.5		13.3		14.6		0.500	0.525
	13	0.50	0.739		106		118		130	0.512	0.537
	14	0.58	0.857		124		137		151	0.551	0.579
9/16		0.60	0.892	14.5		16.8		18.5		0.563	0.591
5/8		0.74	1.101	17.7		20.6		22.7		0.625	0.656
	16	0.75	1.119		161		179		197	0.630	0.661
	18	0.95	1.416		204		226		249	0.709	0.744
	19	1.06	1.578		227		252		278	0.748	0.785
3/4		1.07	1.586	25.6		29.4		32.4		0.750	0.788
	20	1.17	1.748		252		279		308	0.787	0.827
	22	1.42	2.115		305		338		372	0.866	0.909
7/8		1.45	2.159	34.6		39.8		43.8		0.875	0.919
	24	1.69	2.517		363		402		443	0.945	0.992
1		1.89	2.819	44.9		51.7		56.9		1.000	1.050
	26	1.99	2.954		426		472		520	1.024	1.075
	28	2.30	3.426		494		547		603	1.102	1.157
1 1/8		2.40	3.568	56.5		65.0		71.5		1.125	1.181
1 1/4		2.96	4.405	69.4		79.9		87.9		1.250	1.313
	32	3.01	4.475		645		715		787	1.260	1.323
1 3/8		3.58	5.330	83.5		96.0		106		1.375	1.444
	36	3.81	5.664		817		904		997	1.417	1.488
1 1/2		4.26	6.344	98.9		114		125		1.500	1.575
	40	4.70	6.992		1008		1116		1230	1.575	1.654
1 5/8		5.00	7.445	115		132		146		1.625	1.706
	44	5.69	8.460		1220		1351		1489	1.732	1.819
1 3/4		5.80	8.634	133		153		169		1.750	1.838
1 7/8		6.66	9.912	152		174		192		1.875	1.969
	48	6.77	10.068		1452		1608		1772	1.890	1.984
2		7.58	11.277	172		198		217		2.000	2.100
	52	7.94	11.816		1704		1887		2079	2.047	2.150
2 1/8		8.56	12.731	192		221		243		2.125	2.231
	56	9.21	13.704		1976		2188		2411	2.205	2.315
2 1/4		9.59	14.273	215		247		272		2.250	2.363
	60	10.57	15.732		2268		2512		2768	2.362	2.480
2 3/8		10.69	15.903	239		274		301		2.375	2.494

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 18 Classification 8×19 Steel Core

Cross Section Examples		Construction of Rope			Construction of Strand						
		Item	Quantity	Item	Quantity						
		Strands	8	Wires	15 to 26						
		Outer Strands	8	Outer Wires	7 to 12						
		Layer of Strands	1	Layer of Wires	2 to 3						
		Wires in Rope (excluding steel core)	120 to 232								
		Typical Examples		Number of Outer Wires							
		Rope	Strand	Total	Per Strand						
		8×19S	1–9–9	72	9						
		8×21F	1–5–5F–10	80	10						
		8×26WS	1–5–(5+5)–10	80	10						
		8×19W	1–6–(6+6)	96	12						
		8×25F	1–6–6F–12	96	12						
Diameter		Approx. Mass		Minimum Breaking Force ^A					Diameter Range		
in.	[mm]	lb/ft	[kg/m]	IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
1/4	6	0.11	0.161		22.7		25.1		27.7	0.236	0.250
		0.12	0.180	2.94		3.40				0.250	0.265
5/16	7	0.15	0.219		30.9		34.2		37.7	0.276	0.292
		0.19	0.281	4.58		5.27				0.313	0.331
3/8	8	0.19	0.285		40.3		44.7		49.2	0.315	0.331
		0.24	0.361		51.0		56.5		62.3	0.354	0.372
7/16	9	0.27	0.405	6.56		7.55		8.30		0.375	0.394
		0.30	0.446		63.0		69.8		76.9	0.394	0.413
1/2	10	0.36	0.540		76.2		84.4		93.0	0.433	0.455
		0.37	0.551	8.89		10.2		11.2		0.438	0.459
5/8	11	0.43	0.642		90.7		100		111	0.472	0.496
		0.48	0.719	11.5		13.3		14.6		0.500	0.525
3/4	12	0.51	0.754		106		118		130	0.512	0.537
		0.59	0.874		124		137		151	0.551	0.579
7/8	13	0.61	0.910	14.5		16.8		18.5		0.563	0.591
		0.76	1.124	17.7		20.6		22.7		0.625	0.656
1	14	0.77	1.142		161		179		197	0.630	0.661
		0.97	1.445		204		226		249	0.709	0.744
1 1/8	16	1.08	1.610		227		252		278	0.748	0.785
		1.09	1.619	25.6		29.4		32.4		0.750	0.788
1 1/4	18	1.20	1.784		252		279		308	0.787	0.827
		1.45	2.159		305		338		372	0.866	0.909
1 1/2	19	1.48	2.203	34.6		39.8		43.8		0.875	0.919
		1.73	2.569		363		402		443	0.945	0.992
1 3/8	20	1.93	2.877	44.9		51.7		56.9		1.000	1.050
		2.03	3.015		426		472		520	1.024	1.075
1 3/4	22	2.03	3.015		494		547		603	1.102	1.157
		2.45	3.642	56.5		65.0		71.5		1.125	1.181
1 7/8	24	3.02	4.496	69.4		79.9		87.9		1.250	1.313
		3.07	4.567		645		715		787	1.260	1.323
2	26	3.66	5.440	83.5		96.0		106		1.375	1.444
		3.88	5.780		817		904		997	1.417	1.488
2 1/8	28	4.35	6.474	98.9		114		125		1.500	1.575
		4.80	7.136		1008		1116		1230	1.575	1.654
2 1/4	30	5.11	7.598	115		132		146		1.625	1.706
		5.80	8.635		1220		1351		1489	1.732	1.819
2 1/2	32	5.92	8.812	133		153		169		1.750	1.838
		6.80	10.116	152		174		192		1.875	1.969
2 3/8	34	6.91	10.276		1452		1608		1772	1.890	1.984
		7.73	11.510	172		198		217		2.000	2.100
2 3/4	36	8.10	12.060		1704		1887		2079	2.047	2.150
		8.73	12.993	192		221		243		2.125	2.231
3	38	9.40	13.987		1976		2188		2411	2.205	2.315
		9.79	14.567	215		247		272		2.250	2.363
3 1/8	40	10.79	16.056		2268		2512		2768	2.362	2.480
		10.91	16.230	239		274		301		2.375	2.494

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.



TABLE 19 Classification 8×36 Steel Core

Cross Section Examples		Construction of Rope				Construction of Strand					
		Item		Quantity		Item		Quantity			
 <p>8×31 Warrington Seale IWRC</p>		Strands		8		Wires		29 to 57			
		Outer Strands		8		Outer Wires		12 to 18			
		Layer of Strands		1		Layer of Wires		3 to 4			
		Wires in Rope (excluding steel core)		232 to 456							
		Typical Examples				Number of Outer Wires					
		Rope	Strand		Total	Per Strand					
		8×31WS	1–6–(6+6)–12		96	12					
		8×36WS	1–7–(7+7)–14		112	14					
		8×41WS	1–8–(8+8)–16		128	16					
		8×41SF	1–8–8–8F–16		128	16					
		8×49SWS	1–8–8–(8+8)–16		128	16					
		8×46WS	1–9–(9+9)–18		144	18					
Diameter		Approx. Mass		Minimum Breaking Force ^A				Diameter Range			
in.	[mm]	lb/ft	[kg/m]	IPS	1770	EIP	1960	EEIP	2160	Min.	Max.
				Tons	[kN]	Tons	[kN]	Tons	[kN]	in.	in.
1/4	6	0.11	0.161		22.7		25.1		27.7	0.236	0.250
		0.12	0.180	2.94		3.40				0.250	0.265
5/16	7	0.15	0.219		30.9		34.2		37.7	0.276	0.292
		0.19	0.281	4.58		5.27				0.313	0.331
3/8	8	0.19	0.285		40.3		44.7		49.2	0.315	0.331
		0.24	0.361		51.0		56.5		62.3	0.354	0.372
7/16	9	0.27	0.405	6.56		7.55		8.30		0.375	0.394
		0.30	0.446		63.0		69.8		76.9	0.394	0.413
1/2	10	0.36	0.540		76.2		84.4		93.0	0.433	0.455
		0.37	0.551	8.89		10.2		11.2		0.438	0.459
5/8	11	0.43	0.642		90.7		100		111	0.472	0.496
		0.48	0.719	11.5		13.3		14.6		0.500	0.525
3/4	12	0.51	0.754		106		118		130	0.512	0.537
		0.59	0.874		124		137		151	0.551	0.579
7/8	13	0.61	0.910	14.5		16.8		18.5		0.563	0.591
		0.76	1.124	17.7		20.6		22.7		0.625	0.656
1	14	0.77	1.142		161		179		197	0.630	0.661
		0.97	1.445		204		226		249	0.709	0.744
1 1/8	18	1.08	1.610		227		252		278	0.748	0.785
		1.09	1.619	25.6		29.4		32.4		0.750	0.788
1 1/4	20	1.20	1.784		252		279		308	0.787	0.827
		1.45	2.159		305		338		372	0.866	0.909
1 1/2	22	1.48	2.203	34.6		39.8		43.8		0.875	0.919
		1.73	2.569		363		402		443	0.945	0.992
1 3/8	24	1.93	2.877	44.9		51.7		56.9		1.000	1.050
		2.03	3.015		426		472		520	1.024	1.075
1 3/4	26	2.35	3.497		494		547		603	1.102	1.157
		2.45	3.642	56.5		65.0		71.5		1.125	1.181
1 7/8	28	3.02	4.496	69.4		79.9		87.9		1.250	1.313
		3.07	4.567		645		715		787	1.260	1.323
2	32	3.66	5.440	83.5		96.0		106		1.375	1.444
		3.88	5.780		817		904		997	1.417	1.488
2 1/8	36	4.35	6.474	98.9		114		125		1.500	1.575
		4.80	7.136		1008		1116		1230	1.575	1.654
2 1/4	40	5.11	7.598	115		132		146		1.625	1.706
		5.80	8.635		1220		1351		1489	1.732	1.819
2 3/8	44	5.92	8.812	133		153		169		1.750	1.838
		6.80	10.116	152		174		192		1.875	1.969
2 1/2	48	6.91	10.276		1452		1608		1772	1.890	1.984
		7.73	11.510	172		198		217		2.000	2.100
2 5/8	52	8.10	12.060		1704		1887		2079	2.047	2.150
		8.73	12.993	192		221		243		2.125	2.231
2 3/4	56	9.40	13.987		1976		2188		2411	2.205	2.315
		9.79	14.567	215		247		272		2.250	2.363
2 7/8	60	10.79	16.056		2268		2512		2768	2.362	2.480
		10.91	16.230	239		274		301		2.375	2.494

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.



TABLE 20 Classification 8×19 Rotation Resistant—Category 3

Cross Section Examples	Construction of Rope		Construction of Strand					
	Item	Quantity	Item	Quantity				
 8×19 Seale IWRC	Strands	8	Wires	15 to 26				
	Outer Strands	8	Outer Wires	7 to 12				
	Layer of Strands	1	Layer of Wires	2 to 3				
	Wires in Rope (excluding steel core)	120 to 232						
 8×25 Filler Wire IWRC	Typical Examples		Number of Outer Wires					
	Rope	Strand	Total	Per Strand				
	8×19S	1–9–9	72	9				
	8×21F	1–5–5F–10	80	10				
	8×26WS	1–5–(5+5)–10	80	10				
	8×19W	1–6–(6+6)	96	12				
8×25F	1–6–6F–12	96	12					
Diameter		Approx. Mass		Minimum Breaking Force ^A			Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	EIP Tons	EEIP Tons	Min. in.	Max. in.
1/4	6.3	0.12	0.178	2.6	3.0	3.3	0.250	0.265
5/16	7.9	0.18	0.268	4.0	4.6	5.1	0.313	0.331
3/8	9.5	0.26	0.387	5.8	6.6	7.3	0.375	0.394
7/16	11.1	0.36	0.536	7.8	9.0	9.9	0.438	0.459
1/2	12.7	0.47	0.700	10.1	11.6	12.8	0.500	0.525
9/16	14.3	0.60	0.886	12.8	14.7	16.2	0.563	0.591
5/8	15.9	0.74	1.094	15.7	18.1	19.9	0.625	0.656
3/4	19.1	1.06	1.575	22.5	25.9	28.5	0.750	0.788
7/8	22.2	1.44	2.144	30.5	35.0	38.5	0.875	0.919
1	25.4	1.88	2.800	39.6	45.5	50.1	1.000	1.050
1 1/8	28.6	2.38	3.544	49.8	57.3	63.0	1.125	1.181
1 1/4	31.8	2.94	4.375	61.3	70.5	77.6	1.250	1.313
1 3/8	34.9	3.56	5.294	73.8	84.9	93.4	1.375	1.444
1 1/2	38.1	4.23	6.300	87.3	100	110	1.500	1.575

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 21 Classification 19×7 Rotation Resistant—Category 2

Cross Section Examples		Construction of Rope			Construction of Strand						
		Item	Quantity	Item	Quantity						
 18×7 FC	Strands	17 to 18	Wires	5 to 7							
	Outer Strands	10 to 13	Outer Wires	4 to 6							
	Layer of Strands	2	Layer of Wires	1							
	Wires in Rope (excluding steel core)	85 to 126									
 19×7	Typical Examples		Number of Outer Wires								
	Rope	Strand	Total	Per Strand							
	17×7	1–6	66	6							
	18×7	1–6	72	6							
	19×7	1–6	72	6							
Diameter		Approx. Mass				Minimum Breaking Force ^A				Diameter Range	
in.	[mm]	Fiber		WSC		IPS Tons	1770 [kN]	EIP Tons	1960 [kN]	Min. in.	Max. in.
		lb/ft	[kg/m]	lb/ft	[kg/m]						
	6	0.10	0.144	0.10	0.151		20.9		23.1	0.236	0.248
1/4		0.11	0.161	0.11	0.169	2.51		2.77		0.250	0.263
	7	0.13	0.196	0.14	0.205		28.4		31.5	0.276	0.289
5/16		0.17	0.251	0.18	0.264	3.90		4.30		0.313	0.328
	8	0.17	0.255	0.18	0.268		37.2		41.1	0.315	0.331
	9	0.22	0.323	0.23	0.339		47.0		52.1	0.354	0.372
3/8		0.24	0.362	0.26	0.380	5.59		6.15		0.375	0.394
	10	0.27	0.399	0.28	0.419		58.1		64.3	0.394	0.413
	11	0.32	0.483	0.34	0.507		70.2		77.8	0.433	0.455
7/16		0.33	0.493	0.35	0.517	7.58		8.33		0.438	0.459
	12	0.39	0.575	0.41	0.603		83.6		92.6	0.472	0.496
1/2		0.43	0.644	0.45	0.676	9.85		10.8		0.500	0.525
	13	0.45	0.674	0.48	0.708		98.1		109	0.512	0.537
	14	0.53	0.782	0.55	0.821		114		126	0.551	0.579
9/16		0.55	0.814	0.57	0.855	12.4		13.6		0.563	0.591
5/8		0.68	1.006	0.71	1.056	15.3		16.8		0.625	0.656
	16	0.69	1.021	0.72	1.073		149		165	0.630	0.661
	18	0.87	1.293	0.91	1.358		188		208	0.709	0.744
	19	0.97	1.440	1.02	1.513		210		232	0.748	0.785
3/4		0.97	1.448	1.02	1.521	21.8		24.0		0.750	0.788
	20	1.07	1.596	1.13	1.676		232		257	0.787	0.827
	22	1.30	1.931	1.36	2.028		281		311	0.866	0.909
7/8		1.32	1.971	1.39	2.070	29.5		32.5		0.875	0.919
	24	1.54	2.298	1.62	2.413		334		370	0.945	0.992
1		1.73	2.574	1.82	2.703	38.3		42.2		1.000	1.050
	26	1.81	2.697	1.90	2.832		392		435	1.024	1.075
	28	2.10	3.128	2.21	3.285		455		504	1.102	1.157
1 1/8		2.19	3.258	2.30	3.421	48.2		53.1		1.125	1.181
1 1/4		2.70	4.022	2.84	4.224	59.2		65.1		1.250	1.313
	32	2.75	4.086	2.88	4.291		594		658	1.260	1.323
1 3/8		3.27	4.867	3.43	5.111	71.3		78.4		1.375	1.444
	36	3.47	5.171	3.65	5.430		752		833	1.417	1.488
1 1/2		3.89	5.792	4.09	6.082	84.4		92.8		1.500	1.575
1 5/8		4.57	6.800	4.80	7.142	98.4		108.0		1.625	1.706
1 3/4		5.30	7.886	5.57	8.288	114.0		125.0		1.750	1.838

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 22 Classification 34×7 Rotation Resistant—Category 2

Cross Section Examples		Construction of Rope				Construction of Strand					
		Item		Quantity		Item		Quantity			
 34×7 Diameter		Strands		34 to 36		Wires		5 to 9			
		Outer Strands		12 to 18		Outer Wires		4 to 8			
		Layer of Strands		3		Layer of Wires		1			
		Wires in Rope (excluding steel core)		170 to 324							
		Typical Examples				Number of Outer Wires					
		Rope		Strand		Total		Per Strand			
		34×7		1–6		102		6			
		17:11/6–C									
		36×7		1–6		108		6			
		18:12/6–C									
		Approx. Mass				Minimum Breaking Force ^A					
Diameter		Fiber		WSC		1770		1960		Diameter Range	
in.	[mm]	lb/ft	[kg/m]	lb/ft	[kg/m]	Tons	[kN]	Tons	[kN]	in.	in.
1/4	6	0.09	0.140	0.10	0.144	2.55	20.3	2.83	22.4	0.236	0.250
		0.11	0.157	0.11	0.162					0.250	0.265
5/16	7	0.13	0.191	0.13	0.196	3.99	27.6	4.41	30.5	0.276	0.292
		0.17	0.246	0.17	0.253					0.313	0.331
3/8	8	0.17	0.250	0.17	0.257	5.74	36.0	6.36	39.9	0.315	0.331
		0.21	0.316	0.22	0.325					0.354	0.372
7/16	9	0.24	0.354	0.24	0.364	7.81	45.6	8.65	50.5	0.375	0.394
		0.26	0.390	0.27	0.401					0.394	0.413
1/2	10	0.32	0.472	0.33	0.485	10.2	56.3	11.3	62.3	0.433	0.455
		0.32	0.482	0.33	0.495					0.438	0.459
3/4	11	0.38	0.562	0.39	0.577	12.9	68.1	14.3	75.4	0.472	0.496
		0.42	0.629	0.43	0.647					0.500	0.525
5/8	12	0.44	0.659	0.46	0.678	15.9	81.1	17.7	89.8	0.512	0.537
		0.51	0.764	0.53	0.786					0.551	0.579
7/8	13	0.53	0.796	0.55	0.819	23.0	95.1	25.4	105.3	0.563	0.591
		0.66	0.983	0.68	1.011					0.625	0.656
1	14	0.67	0.998	0.69	1.027	31.3	110	17.7	122	0.630	0.661
		0.85	1.264	0.87	1.299					0.709	0.744
1 1/8	16	0.95	1.408	0.97	1.448	40.8	144	25.4	160	0.748	0.785
		0.95	1.415	0.98	1.455					0.750	0.788
1 1/4	18	1.05	1.560	1.08	1.604	48.8	182	25.4	202	0.787	0.827
		1.27	1.888	1.30	1.941					0.866	0.909
1 3/8	19	1.29	1.926	1.33	1.981	51.7	203	25.4	225	0.875	0.919
		1.51	2.246	1.55	2.310					0.945	0.992
1 1/2	20	1.69	2.516	1.74	2.587	63.8	324	25.4	302	1.000	1.050
		1.77	2.636	1.82	2.711					1.024	1.075
1 5/8	22	2.05	3.058	2.11	3.144	77.2	441	25.4	489	1.102	1.157
		2.14	3.184	2.20	3.274					1.125	1.181
1 3/4	24	2.64	3.931	2.72	4.042	91.8	576	25.4	638	1.250	1.313
		2.68	3.994	2.76	4.106					1.260	1.323
1 7/8	26	3.20	4.757	3.29	4.891	108	729	25.4	808	1.375	1.444
		3.40	5.054	3.49	5.197					1.417	1.488
2	28	3.80	5.661	3.91	5.821	108	901	25.4	997	1.500	1.575
		4.19	6.240	4.31	6.416					1.575	1.654
1 5/8	40	4.46	6.644	4.59	6.832	108	901	119	997	1.625	1.706

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 23 Classification 35×7 Rotation Resistant—Category 1

Cross Section Examples		Construction of Rope		Construction of Strand							
		Item	Quantity	Item	Quantity						
		Strands	35	Wires	5 to 9						
		Outer Strands	16	Outer Wires	4 to 8						
		Layer of Strands	3	Layer of Wires	1						
		Wires in Rope (excluding steel core)	238								
35×7		Typical Examples		Number of Outer Wires							
		Rope 35×7	Strand 1–6	Total 96	Per Strand 6						
Diameter		Approx. Mass		Minimum Breaking Force ^A				Diameter Range			
in.	[mm]	WSC		1770		1960		2160		Min. in.	Max. in.
		lb/ft	[kg/m]	Tons	[kN]	Tons	[kN]	Tons	[kN]		
3/8	9	0.25	0.369		55.4		60.2		66.6	0.354	0.372
		0.28	0.413	6.98		7.46		8.22		0.375	0.394
7/16	10	0.31	0.455		69.2		75.4		83.5	0.394	0.413
	11	0.37	0.551		83.1		90.6		100	0.433	0.455
1/2	12	0.38	0.562	9.53		10.1		11.2		0.438	0.459
		0.44	0.655		99.9		106		119	0.472	0.496
9/16	13	0.49	0.734	12.6		13.6		14.6		0.500	0.525
		0.52	0.769		117		127		142	0.512	0.537
5/8	14	0.60	0.892		136		147		165	0.551	0.579
		0.62	0.929	15.9		17.3		18.5		0.563	0.591
3/4	16	0.77	1.147	19.7		21.7		22.8		0.625	0.656
		0.78	1.165		178		193		217	0.630	0.661
7/8	18	0.99	1.474		223		241		271	0.709	0.744
		1.10	1.643	28.4		251		275		0.748	0.785
1	20	1.11	1.651		278	30.9		32.9		0.750	0.788
		1.22	1.820		278		299		336	0.787	0.827
1 1/8	22	1.48	2.202		337		368		413	0.866	0.909
		1.51	2.247	38.7		41.6		44.7		0.875	0.919
1 1/4	24	1.76	2.621		401		439		493	0.945	0.992
		1.97	2.935	50.3		54.4		58.4		1.000	1.050
1 1/2	26	2.07	3.076		469		514		576	1.024	1.075
		2.40	3.567		549		596		646	1.102	1.157
1 3/8	28	2.50	3.715	64.3		68.9		73.9		1.125	1.181
		3.08	4.587	78.8		86		91.3		1.250	1.313
1 3/4	32	3.13	4.659		711		765		829	1.260	1.323
		3.73	5.550	95.4		106		110		1.375	1.444
1 7/8	36	3.96	5.897		906		977		1060	1.417	1.488
		4.44	6.605	114		120		131		1.500	1.575
2	40	4.89	7.280		1112		1200		1300	1.575	1.654
		5.21	7.752	134		140		154		1.625	1.706

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.


Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 24 Classification 6×12 Fiber Core

Cross Section Examples		Construction of Rope		Construction of Strand			
		Item	Quantity	Item	Quantity		
	6×12 Running Rope FC	Strands	6	Wires	12		
		Outer Strands	6	Outer Wires	12		
		Layer of Strands	1	Layer of Wires	1		
		Wires in Rope (excluding steel core)	72				
		Typical Examples		Number of Outer Wires			
		Rope	Strand	Total	per Strand		
		6×12	FC-12	72	12		
Diameter		Approx. Mass		Minimum Breaking Force		Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	Min. in.	Max. in.	
5/16	7.9	0.10	0.152	2	0.313	0.328	
3/8	9.5	0.15	0.219	3.36	0.375	0.394	
7/16	11.1	0.20	0.298	4.55	0.438	0.459	
1/2	12.7	0.26	0.389	5.91	0.500	0.525	
9/16	14.3	0.33	0.492	7.45	0.563	0.591	
5/8	15.9	0.41	0.607	9.16	0.625	0.656	
3/4	19.1	0.59	0.875	13.1	0.750	0.788	
13/16	20.6	0.69	1.026	15.3	0.813	0.853	
7/8	22.2	0.80	1.190	17.7	0.875	0.919	
1	25.4	1.04	1.555	23.0	1.000	1.050	



Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 25 Classification 6×24 Fiber Core

Cross Section Examples		Construction of Rope			Construction of Strand	
		Item	Quantity	Item	Quantity	
		Strands	6	Wires	24	
		Outer Strands	6	Outer Wires	12–16	
		Layer of Strands	1	Layer of Wires	2	
		Wires in Rope (excluding steel core)	144			
			Typical Examples		Number of Outer Wires	
		Rope	Strand	Total	per Strand	
		6×24	FC/9/15	90	15	
		6×24W	FC/8-(8+8)	96	16	
		6×24S	FC/12-12	72	12	
6×24 (2 operation) Hawser Rope FC		Diameter	Approx. Mass	Minimum Breaking Force	Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS	Min.	Max.
				Tons	in.	in.
3/8	9.5	0.19	0.289	4.77	0.375	0.394
1/2	12.7	0.34	0.513	8.40	0.500	0.525
9/16	14.3	0.44	0.649	10.6	0.563	0.591
5/8	15.9	0.54	0.801	13.0	0.625	0.656
3/4	19.1	0.78	1.154	18.6	0.750	0.788
7/8	22.2	1.06	1.571	25.2	0.875	0.919
1	25.4	1.38	2.052	32.8	1.000	1.050
1 1/8	28.6	1.74	2.597	41.2	1.125	1.181
1 1/4	31.8	2.15	3.206	50.7	1.250	1.313
1 3/8	34.9	2.61	3.879	61.0	1.375	1.444
1 1/2	38.1	3.10	4.616	72.3	1.500	1.575
1 5/8	41.3	3.64	5.418	84.5	1.625	1.706
1 3/4	44.5	4.22	6.283	97.5	1.750	1.838
1 7/8	47.6	4.85	7.213	111	1.875	1.969
2	50.8	5.51	8.206	126	2.000	2.100
2 1/16	52.4	5.87	8.734	134	2.063	2.166

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 26 Classification 6×25 Triangular Strand Fiber Core

Cross Section Examples		Construction of Rope		Construction of Strand				
		Item	Quantity	Item	Quantity			
 6×30 Style G Flattened Strand (Plaited Center) FC	Strands	6	Wires	144				
	Outer Strands	6	Outer Wires	72				
	Layer of Strands	1	Layer of Wires	2				
	Wires in Rope							
 6×31 Style V (Brangle Center) FC	Typical Examples		Number of Outer Wires					
	Rope	Strand	Total	Per Strand				
	6×25B	1/12/12	72	12				
	6×30G	(3×2)/12/12	72	12				
	6×27H	3/12/12	72	12				
6×31V	1-6/12/12	72	12					
Diameter		Approx. Mass		Minimum Breaking Force ^A			Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	EIP Tons	EEIP Tons	Min. in.	Max. in.
3/8	9.5	0.25	0.372	6.7	7.4	8.1	0.325	0.394
1/2	12.7	0.45	0.669	11.8	13.0	14.3	0.500	0.525
9/16	14.3	0.57	0.847	14.9	16.4	18.0	0.563	0.591
5/8	15.9	0.70	1.046	18.3	20.1	22.1	0.625	0.656
3/4	19.1	1.01	1.506	26.2	28.8	31.7	0.750	0.788
7/8	22.2	1.38	2.050	35.4	38.9	42.8	0.875	0.919
1	25.4	1.80	2.677	46.0	50.6	55.7	1.000	1.050
1 1/8	28.6	2.28	3.389	57.9	63.7	70.1	1.125	1.181
1 1/4	31.8	2.81	4.183	71.0	78.1	85.9	1.250	1.313
1 3/8	34.9	3.40	5.062	85.5	94.1	103	1.375	1.444
1 1/2	38.1	4.05	6.024	101	111	122	1.500	1.575
1 5/8	41.3	4.75	7.070	118	130	143	1.625	1.706
1 3/4	44.5	5.51	8.200	138	152	167	1.750	1.838
1 7/8	47.6	6.33	9.413	155	171	188	1.875	1.969
2	50.8	7.20	10.710	176	194	213	2.000	2.100
2 1/8	54.0	8.12	12.090	196	215	237	2.125	2.231
2 1/4	57.2	9.11	13.554	220	240	264	2.250	2.363
2 3/8	60.3	10.15	15.102	241	265	292	2.375	2.494
2 1/2	63.5	11.20	16.665	269	295	325	2.500	2.625
2 3/4	69.8	13.60	20.237	321	354	389	2.750	2.888

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 27 Classification 6×25 Triangular Strand Steel Core

Cross Section Examples		Construction of Rope			Construction of Strand				
		Item	Quantity		Item	Quantity			
		Strands	6		Wires	144			
		Outer Strands	6		Outer Wires	72			
		Layer of Strands	1		Layer of Wires	2			
		Wires in Rope							
6×30 Style G Flattened Strand (Plated Center) IWRC Diameter		Typical Examples			Number of Outer Wires				
		Rope	Strand	Total	Per Strand				
		6×25B	1/12/12	72	12				
		6×30G	(3×2)/12/12	72	12				
		6×27H	3/12/12	72	12				
6×31V	1-6/12/12	72	12						
		Approx. Mass			Minimum Breaking Force ^A			Diameter Range	
in.	[mm]	lb/ft	[kg/m]	IPS Tons	EIP Tons	EEIP Tons	Min. in.	Max. in.	
3/8	9.5	0.26	0.387	7.2	7.9	8.7	0.375	0.394	
1/2	12.7	0.47	0.703	12.6	14.0	15.4	0.500	0.525	
5/16	14.3	0.60	0.890	16.0	17.6	19.4	0.563	0.591	
5/8	15.9	0.74	1.099	19.6	21.7	23.9	0.625	0.656	
3/4	19.1	1.06	1.582	28.1	31.0	34.1	0.750	0.788	
7/8	22.2	1.45	2.154	38.0	41.9	46.1	0.875	0.919	
1	25.4	1.89	2.813	49.4	54.4	59.8	1.000	1.050	
1 1/8	28.6	2.39	3.560	62.2	68.5	75.4	1.125	1.181	
1 1/4	31.8	2.95	4.395	76.3	84.0	92.4	1.250	1.313	
1 3/8	34.9	3.57	5.318	91.9	101	111	1.375	1.444	
1 1/2	38.1	4.25	6.329	108	119	131	1.500	1.575	
1 5/8	41.3	4.99	7.428	127	140	154	1.625	1.706	
1 3/4	44.5	5.79	8.615	146	161	177	1.750	1.838	
1 7/8	47.6	6.65	9.889	167	184	202	1.875	1.969	
2	50.8	7.56	11.252	189	207	228	2.000	2.100	
2 1/8	54.0	8.54	12.702	211	232	255	2.125	2.231	
2 1/4	57.2	9.57	14.240	237	260	286	2.250	2.363	
2 3/8	60.3	10.66	15.867	261	287	316	2.375	2.494	
2 1/2	63.5	11.80	17.558	289	318	350	2.500	2.625	
2 3/4	69.8	14.30	21.278	345	381	418	2.750	2.888	

^A Minimum breaking force for final-galvanized ropes 10 % lower than values listed.


Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 28 Classification 6×19 Compacted Strand (CS)

Cross Section Examples		Construction of Rope				Construction of Strand				
		Item		Quantity		Item		Quantity		
 <p>6×26 Warrington Seale Compacted Strand IWRC</p>		Strands	6		Wires	15 to 26				
		Outer Strands	6		Outer Wires	7 to 12				
		Layer of Strands	1		Layer of Wires	2 to 3				
		Wires in Rope	90 to 156							
		Typical Examples				Number of Outer Wires				
		Rope	Strand		Total	Per Strand				
		6×19S	1-9-9		54	9				
		6×21F	1-5-5F-10		60	10				
		6×26WS	1-5-(5+5)-10		60	10				
		6×19W	1-6-(6+6)		72	12				
6×25F	1-6-6F-12		72	12						
Diameter		Approx. Mass		Minimum Breaking Force				Diameter Range		
in.	[mm]	lb/ft	[kg/m]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.	
3/8	10	0.282	0.419	8.30	85.3	9.13	91.5	0.375	0.394	
	11	0.310	0.462					0.394	0.413	
7/16	12	0.376	0.559	11.2	98.1	12.3	113	0.433	0.455	
	13	0.447	0.665					0.438	0.459	
1/2	14	0.501	0.745	14.6	114	16.1	127	0.472	0.496	
	15	0.525	0.781					0.500	0.525	
9/16	16	0.609	0.906	18.5	147	20.4	157	0.512	0.537	
	17	0.634	0.943					0.551	0.579	
5/8	18	0.782	1.164	22.7	169	25.0	183	0.563	0.591	
	19	0.795	1.183					0.625	0.656	
3/4	20	1.006	1.497	32.4	217	35.6	228	0.630	0.661	
	21	1.068	1.668					0.709	0.744	
7/8	22	1.121	1.668	43.8	302	48.2	323	0.748	0.785	
	23	1.127	1.677					0.750	0.788	
1	24	1.242	1.848	56.9	333	62.6	355	0.787	0.827	
	25	1.503	2.236					0.866	0.909	
1 1/8	26	1.534	2.282	71.5	398	78.7	423	0.875	0.919	
	27	1.788	2.661					0.945	0.992	
1 1/4	28	2.003	2.981	87.9	487	96.7	518	1.000	1.050	
	29	2.099	3.123					1.024	1.075	
1 3/8	30	2.434	3.622	106	576	117	610	1.102	1.157	
	31	2.535	3.772					1.125	1.181	
1 1/2	32	3.130	4.657	125	844	138	914	1.250	1.313	
	33	3.179	4.731					1.260	1.323	
1 5/8	34	3.787	5.635	146	1060	178.7	1120	1.375	1.444	
	35	4.024	5.988					1.417	1.488	
1 3/4	36	4.507	6.706	169	1290	211	1320	1.500	1.575	
	37	4.570	6.706					1.575	1.654	
1 7/8	38	4.967	7.392	192	1500	239	1590	1.625	1.706	
	39	5.289	7.871					1.625	1.706	
2	40	6.011	8.944	217	1880	299	1890	1.732	1.819	
	41	6.134	9.128					1.750	1.838	
2 1/8	42	6.134	9.128	243	2130	267	2220	1.750	1.838	
	43	7.042	10.479					1.875	1.969	
2 1/4	44	7.153	10.644	272	2470	299	2574	1.890	1.984	
	45	8.012	11.923					2.000	2.100	
2 3/8	46	8.395	12.492	243	2130	267	2220	2.047	2.150	
	47	9.045	13.460					2.125	2.231	
2 1/2	48	9.736	14.488	272	2470	299	2574	2.205	2.315	
	49	10.140	15.090					2.250	2.363	


Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 29 Classification 6×36 Compacted Strand (CS)

Cross Section Examples		Construction of Rope				Construction of Strand					
		Item		Quantity		Item		Quantity			
 <p>6×36 Compacted Strand</p>		Strands	6		Wires	27 to 49					
		Outer Strands	6		Outer Wires	12 to 18					
		Layer of Strands	1		Layer of Wires	27 to 49					
		Wires in Rope	156 to 276								
		Typical Examples				Number of Outer Wires					
		Rope	Strand		Total	Per Strand					
		6×31WS	1-6-(6+6)-12		72	12					
		6×36WS	1-7-(7+7)-14		84	14					
		6×41WS	1-8-(8+8)-16		96	16					
		6×41SF	1-8-8-8F-16		96	16					
6×49SWS	1-8-8-(8+8)-16		96	16							
6×46WS	1-9-(9+9)-18		108	18							
Diameter		Approx. Mass		Minimum Breaking Force				Diameter Range			
in.	[mm]	lb/ft	[kg/m]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.		
3/8	10	0.282	0.419	8.30	85.3	9.13	91.5	0.375	0.394		
	11	0.310	0.462		98.1			113	0.394	0.413	
7/16	12	0.376	0.559	11.2	114	12.3	127	0.433	0.455		
	13	0.383	0.571		147			161	0.438	0.459	
1/2	14	0.447	0.665	14.6	169	16.1	183	0.472	0.496		
	16	0.501	0.745		217			25.0	0.500	0.525	
5/8	18	0.525	0.781	18.5	275	20.4	298	0.512	0.537		
	19	0.609	0.906		302			323	0.551	0.579	
3/4	20	0.634	0.943	22.7	333	35.6	355	0.563	0.591		
	22	0.782	1.164		398			423	0.625	0.656	
7/8	24	0.795	1.183	32.4	487	48.2	518	0.630	0.661		
	26	1.006	1.497		576			610	0.709	0.744	
1	28	1.121	1.668	43.8	655	62.6	700	0.748	0.785		
	32	1.127	1.677		844			914	0.750	0.788	
1 1/8	36	1.242	1.848	56.9	1060	117	1120	0.787	0.827		
	40	1.503	2.236		1290			138	1.000	1.050	
1 1/4	44	1.534	2.282	71.5	1500	138	1590	0.866	0.909		
	48	1.788	2.661		1880			211	0.875	0.919	
1 3/8	52	2.003	2.981	87.9	2130	239	2220	0.945	0.992		
	56	2.099	3.123		2470			267	1.000	1.050	
1 1/2	60	2.434	3.622	106	2750	267	2574	1.024	1.075		
	64	2.535	3.772		3230			299	1.102	1.157	
1 3/4	72	3.130	4.657	125	3540	356	3550	1.125	1.181		
	76	3.179	4.731		4230			399	1.250	1.313	
1 7/8	84	3.787	5.635	146	4230	423	4230	1.260	1.323		
	88	4.024	5.988		4870			487	1.375	1.444	
2	96	4.507	6.706	192	5180	518	5180	1.417	1.488		
	100	4.967	7.392		6100			610	1.500	1.575	
2 1/8	108	5.289	7.871	217	6550	655	6550	1.575	1.654		
	112	6.011	8.944		7710			771	1.625	1.706	
2 1/4	120	6.134	9.128	243	8440	844	8440	1.732	1.819		
	124	6.134	9.128		9900			990	1.750	1.838	
2 3/8	132	7.042	10.479	272	11200	1120	11200	1.875	1.969		
	136	7.153	10.644		13200			1320	1.890	1.984	
2 3/4	144	8.012	11.923	324	15900	1590	15900	2.000	2.100		
	148	8.395	12.492		18800			1880	2.047	2.150	
3	156	9.045	13.460	396	22200	2220	22200	2.125	2.231		
	160	9.736	14.488		26700			2670	2.125	2.231	
3 1/8	168	10.140	15.090	474	29900	2990	29900	2.205	2.315		
	172	10.140	15.090		35400			3540	2.205	2.315	

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


TABLE 30 Classification 6×19 Swaged Rope (SW)

Cross Section Examples		Construction of Rope		Construction of Strand			
		Item	Quantity	Item	Quantity		
 <p>6×26 Warrington Compacted (Swaged) IWRC</p>	Strands	6	Wires	15–26			
	Outer Strands	6	Outer Wires	7–12			
	Layer of Strands	1	Layer of Wires	2–3			
	Wires in Rope (excluding steel core)	90–156					
	Typical Examples		Number of Outer Wires				
	Rope	Strand	Total	per Strand			
	6×19S	1–9–9	54	9			
	6×21F	1–5–5F–10	60	10			
	6×26WS	1–5–(5+5)–10	60	10			
	6×19W	1–6–(6+6)	72	12			
	6×25F	1–6–6F–12	72	12			
Diameter		Approx. Mass		Minimum Breaking Force		Diameter Range	
in.	[mm]	lb/ft	[kg/m]	EIP Tons	Min. in.	Max. in.	
½	12.7	0.55	0.826	15.5	0.500	0.525	
⅝	14.3	0.70	1.045	19.6	0.563	0.591	
⅞	15.9	0.87	1.290	24.2	0.625	0.656	
¾	19.1	1.25	1.858	34.9	0.750	0.788	
⅞	22.2	1.70	2.529	47.4	0.875	0.919	
1	25.4	2.22	3.303	62.0	1.000	1.050	
1⅛	28.6	2.81	4.181	73.5	1.125	1.181	
1¼	31.8	3.47	5.161	90.0	1.250	1.313	
1⅝	34.9	4.20	6.245	106	1.375	1.444	
1½	38.1	4.99	7.432	130	1.500	1.575	

Note—To convert to kilonewtons (kN), multiply tons by 8.896.

Note—Also called compacted rope.



TABLE 31 Classification 6×36 Swaged Rope (SW)

Cross Section Examples		Construction of Rope			Construction of Strand	
		Item	Quantity	Item	Quantity	
 <p>6×31 Warrington Seale Compacted (Swaged) IWRC</p>	Strands	6	Wires	27–49		
	Outer Strands	6	Outer Wires	12–18		
	Layer of Strands	1	Layer of Wires	3–4		
	Wires in Rope (excluding steel core)	156–276				
	Typical Examples			Number of Outer Wires		
	Rope	Strand	Total	per Strand		
6×31WS	1–6–(6+6)–12	72	12			
6×36WS	1–7–(7+7)–14	84	14			
6×41WS	1–8–(8+8)–16	96	16			
6×41SF	1–8–8F–16	96	16			
6×49SWS	1–8–8–(8+8)–16	96	16			
6×46WS	1–9–(9+9)–18	108	18			
Diameter		Approx. Mass		Minimum Breaking Force	Diameter Range	
in.	[mm]	lb/ft	[kg/m]	EIP Tons	Min. in.	Max. in.
1/2	12.7	0.55	0.826	15.5	0.500	0.525
9/16	14.3	0.70	1.045	19.6	0.563	0.591
5/8	15.9	0.87	1.290	24.2	0.625	0.656
3/4	19.1	1.25	1.858	34.9	0.750	0.788
7/8	22.2	1.70	2.529	47.4	0.875	0.919
1	25.4	2.22	3.303	62.0	1.000	1.050
1 1/8	28.6	2.81	4.181	73.5	1.125	1.181
1 1/4	31.8	3.47	5.161	90.0	1.250	1.313
1 3/8	34.9	4.20	6.245	106	1.375	1.444
1 1/2	38.1	4.99	7.432	130	1.500	1.575

Note—To convert to kilonewtons (kN), multiply tons by 8.896.


Note—Also called compacted rope.

TABLE 32 Classification 19×7 Compacted Strand (CS) Rotation Resistant—Category 2

Cross Section Examples		Construction of Rope		Construction of Strand					
		Item	Quantity	Item	Quantity				
 18×7 Compacted Strand		Strands	17 to 18	Wires	5 to 7				
		Outer Strands	10 to 13	Outer Wires	4 to 6				
		Layer of Strands	2	Layer of Wires	1				
		Wires in Rope (excluding steel core)	85 to 126						
 19×7 Compacted Strand Diameter		Typical Examples		Number of Outer Wires					
		Rope	Strand	Total	Per Strand				
		17×7	1–6	66	6				
		18×7	1–6	72	6				
		19×7	1–6	72	6				
		Approx. Mass		Minimum Breaking Force		Diameter Range			
in.	[mm]	lb/ft	[kg/m]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
	6	0.12	0.181		30.7		34.0	0.236	0.248
1/4	7	0.14	0.203	3.74		4.11		0.250	0.263
	7	0.17	0.247		39.8		44.1	0.276	0.289
5/16	8	0.21	0.318	5.80		6.38		0.313	0.328
	8	0.22	0.323		54.2		60.0	0.315	0.331
	9	0.27	0.408		67.6		74.8	0.354	0.372
3/8	9	0.31	0.457	7.55		8.30		0.375	0.394
	10	0.34	0.504		84.3		93.3	0.394	0.413
	11	0.41	0.610		105		116	0.433	0.455
7/16	11	0.42	0.622	10.2		11.2		0.438	0.459
	12	0.49	0.726		121		133	0.472	0.496
1/2	12	0.55	0.813	13.3		14.6		0.500	0.525
	13	0.57	0.852		147		162	0.512	0.537
	14	0.66	0.988		167		185	0.551	0.579
9/16	14	0.69	1.029	16.8		18.5		0.563	0.591
5/8	14	0.85	1.270	20.6		22.7		0.625	0.656
	16	0.87	1.290		219		243	0.630	0.661
	18	1.10	1.633		278		308	0.709	0.744
	19	1.22	1.819		304		337	0.748	0.785
3/4	19	1.23	1.829	29.4		32.4		0.750	0.788
	20	1.35	2.016		336		372	0.787	0.827
	22	1.64	2.439		412		457	0.866	0.909
7/8	22	1.67	2.490	39.8		43.8		0.875	0.919
	24	1.95	2.903		476		541	0.945	0.992
1	24	2.19	3.252	51.7		56.9		1.000	1.050


Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 33 Classification 19×19 Compacted Strand (CS) Rotation Resistant—Category 2

Cross Section Examples		Construction of Rope				Construction of Strand			
		Item		Quantity		Item		Quantity	
 <p>19×19 Seale Compacted Strand</p>		Strands		17 to 18		Wires		15 to 26	
		Outer Strands		10 to 13		Outer Wires		7 to 12	
		Layer of Strands		2		Layer of Wires		2 to 3	
		Wires in Rope (excluding steel core)		255 to 468					
				Typical Examples				Number of Outer Wires	
		Rope		Strand		Total		Per Strand	
		17×19S		1–9–9		99		9	
		18×19S		1–9–9		108		9	
		18×26WS		1–5–(5+5)–10		120		10	
		19×19S		1–9–9		108		9	
		19×26WS		1–5–(5+5)–10		120		10	
Diameter		Approx. Mass		Minimum Breaking Force				Diameter Range	
in.	[mm]	lb/ft	[kg/m]	EIP Tons	1960 [kN]	EEIP Tons	2160 [kN]	Min. in.	Max. in.
3/8	10	0.31	0.462	7.55	84.3	8.3	93.3	0.375	0.394
	11	0.34	0.509					0.394	0.413
7/16	12	0.41	0.616	10.2	105	11.2	116	0.433	0.455
	13	0.42	0.629					0.438	0.459
1/2	14	0.49	0.733	13.3	121	14.6	133	0.472	0.496
	15	0.55	0.821					0.500	0.525
9/16	16	0.58	0.860	16.8	147	18.5	162	0.512	0.537
	17	0.67	0.998					0.551	0.579
5/8	18	0.70	1.039	20.6	160	22.7	180	0.563	0.591
	19	0.86	1.283					0.625	0.656
3/4	20	0.88	1.303	29.4	215	32.4	241	0.630	0.661
	21	1.11	1.649					0.709	0.744
7/8	22	1.23	1.837	39.8	300	43.8	337	0.748	0.785
	23	1.24	1.847					0.750	0.788
1	24	1.37	2.036	51.7	335	56.9	376	0.787	0.827
	25	1.66	2.464					0.866	0.909
1 1/8	26	1.69	2.514	79.9	405	87.9	454	0.875	0.919
	27	1.97	2.932					0.945	0.992
1 1/4	28	2.21	3.284	96.0	482	106	540	1.000	1.050
	29	2.31	3.441					1.024	1.075
1 3/8	30	2.68	3.991	114	572	125	637	1.102	1.157
	31	2.79	4.156					1.125	1.181
1 1/2	32	3.45	5.131	132	662	145	743	1.250	1.313
	33	3.50	5.212					1.260	1.323
1 5/8	34	3.50	5.212	132	859	106	964	1.260	1.323
	35	4.17	6.209					1.375	1.444
1 3/4	36	4.43	6.597	132	1085	125	1218	1.417	1.488
	37	4.97	7.389					1.500	1.575
1 7/8	38	5.47	8.144	132	1340	145	1503	1.575	1.654
	39	5.83	8.671					1.625	1.706

Note—To convert to kilonewtons (kN), multiply tons by 8.896.

TABLE 34 Classification 35×7 Compacted Strand (CS) Rotation Resistant—Category 1

Cross Section Examples		Construction of Rope				Construction of Strand			
		Item		Quantity		Item		Quantity	
		Strands		35		Wires		5 to 9	
		Outer Strands		16		Outer Wires		4 to 8	
		Layer of Strands		3		Layer of Wires		1	
		Wires in Rope		238					
35×7 Compacted Strand		Typical Examples				Number of Outer Wires			
		Rope 35×7		Strand 1–6		Total 96		Per Strand 6	
Diameter		Approx. Mass		Minimum Breaking Force				Diameter Range	
in.	[mm]	lb/ft	[kg/m]	1960		2160		Min. in.	Max. in.
				Tons	[kN]	Tons	[kN]		
7/16	10	0.33	0.497		87.6		98.3	0.394	0.413
	11	0.40	0.601		105		118	0.433	0.455
1/2	12	0.41	0.614	12.1		13.4		0.438	0.459
	13	0.48	0.716		124		140	0.472	0.496
9/16	14	0.54	0.802	15.4		17.4		0.500	0.525
	13	0.56	0.840		144		162	0.512	0.537
5/8	14	0.65	0.974		168		188	0.551	0.579
	16	0.68	1.015	19.7		22.0		0.563	0.591
3/4	16	0.84	1.253	25.2		28.2		0.625	0.656
	18	0.85	1.272		224		251	0.630	0.661
7/8	18	1.08	1.610		274		308	0.709	0.744
	19	1.21	1.794		307		344	0.748	0.785
1	19	1.21	1.804	34.5		38.7		0.750	0.788
	20	1.34	1.988		341		382	0.787	0.827
1 1/8	22	1.62	2.405		415		466	0.866	0.909
	24	1.65	2.455	47.2		53.0		0.875	0.919
1 1/4	24	1.92	2.863		491		555	0.945	0.992
	26	2.15	3.206	62.4		70.0		1.000	1.050
1 3/8	26	2.26	3.360		588		660	1.024	1.075
	28	2.62	3.896		676		758	1.102	1.157
1 3/4	28	2.73	4.058	77.5		86.9		1.125	1.181
	32	3.37	5.010	98.1		110		1.250	1.313
1 7/8	32	3.42	5.089		873		980	1.260	1.323
	36	4.07	6.062	117		124		1.375	1.444
1 7/8	36	4.33	6.441		1110		1232	1.417	1.488
	40	4.85	7.215	138		147		1.500	1.575
1 7/8	40	5.34	7.952		1390		1521	1.575	1.654
	40	5.69	8.467	167		182		1.625	1.706

Note—To convert to kilonewtons (kN), multiply tons by 8.896.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A1023/A1023M – 07) that may impact the use of this standard. (Approved October 1, 2009.)

- (1) Revised tables **Table 12, Table 13, Table 14, Table 15, Table 20, Table 21, Table 25, Table 26, and Table 27.** (2) Corrected typographical error in heading of **Table 18.**

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT).